

Report No. SZABB190109001-01

Page 1 of 17

锂电池 UN38.3 测试报告 Lithium Battery UN38.3 Test Report

委托单位(Client) : 深圳市电科电源股份有限公司

BST POWER (SHENZHEN) LIMITED

生产工厂

工) : 衡阳力赛储能有限公司 (Manufacturer)

Hengyang LC Energy Storage Limited

样品名称(Product) : 锂离子电芯

Li-ion Cell

样品型号(Model) : IFR18650E1500

样品接收日期 : 2019年01月12日

Date of Sample Received Jan. 12, 2019

检测日期 : 2019年01月12日至2019年01月24日

Date of Test Jan. 12, 2019 to Jan. 24, 2019

报告日期 : 2019年01月24日 Date of Report Jan. 24, 2019

批准

(Approved Signatory) 审核

(Checked by)

检测

(Tested by)

加德克

报告专用章 Stamp





Report No. SZABB190109001-01

Page 2 of 17

1. 样品描述(SAMPLE DESCRIPTION):

	11			
锂离子电芯	Anbo	电芯型号:	IFR18650E1500	TUP JEK
Li-ion Cell		Cell Model	nbotek	
深圳市电科	电源股份有限公司	ek Aupo	k sotek	Anbot
BST POW	ER (SHENZHEN) LIN	NITED MIDOL		
深圳市龙岗	区横岗街道大康社区	新龙路 37 号	otek Anbot	N. Dr.
37#Xinlong	g Rd, Dakang, Hengg	ang, Longgang, Sh	enzhen, P. R. China	a ^{ter}
衡阳力赛储	能有限公司	And	abotek P	'upo.
Hengyang	LC Energy Storage L	imited No.		
3.2V	额定容量:	1500mAh	商标:	1 abote
Net Vare	Rated Capacity	4.8Wh	Trademark	VI.
300mA	最大连续	1500mA	充电截止电流:	15mA
upos		Anboten And	End Charge	tek
Anboter	Continuous Charge Current	Anbotek A	Current	botek
2.0V	最大放电电流:	4500mA	充电限制电压:	3.65V
Anb	Maximum Discharge Current	k Anbotek	Limited Charge Voltage	Andobote
2019年01	月12日	测试结束日期	2019年01月24日	Air
Jan. 12, 20	19 botek Ant	Finished date	Jan. 24, 2019	
	Li-ion Cell 深圳市电科 BST POW 深圳市龙岗 37#Xinlong 衡阳力赛储 Hengyang 3.2V 300mA	深圳市电科电源股份有限公司 BST POWER (SHENZHEN) LIM 深圳市龙岗区横岗街道大康社区 37#Xinlong Rd, Dakang, Hengg 衡阳力赛储能有限公司 Hengyang LC Energy Storage L 3.2V 额定容量: Rated Capacity 300mA 最大连续 充电电流: Maximum Continuous Charge Current 2.0V 最大放电电流: Maximum	Li-ion Cell 深圳市电科电源股份有限公司 BST POWER (SHENZHEN) LIMITED 深圳市龙岗区横岗街道大康社区新龙路 37 号 37#Xinlong Rd, Dakang, Henggang, Longgang, Sh 衡阳力赛储能有限公司 Hengyang LC Energy Storage Limited 3.2V 额定容量: 1500mAh Rated Capacity 4.8Wh 300mA 最大连续 充电电流: Maximum Continuous Charge Current 2.0V 最大放电电流: 4500mA Maximum Discharge Current 2019年01月12日 测试结束日期	Li-ion CellCell Model深圳市电科电源股份有限公司BST POWER (SHENZHEN) LIMITED深圳市龙岗区横岗街道大康社区新龙路 37 号37#Xinlong Rd, Dakang, Henggang, Longgang, Shenzhen, P. R. China衡阳力赛储能有限公司Hengyang LC Energy Storage Limited3.2V额定容量:1500mAh商标:Rated Capacity4.8WhTrademark300mA最大连续 充电电流: Maximum Continuous Charge Current1500mA充电截止电流: End Charge Current2.0V最大放电电流: Maximum Discharge Current4500mA充电限制电压: Limited Charge Voltage2019年01月12日测试结束日期2019年01月24日

2. 参考方法 (REFERENCE METHOD)

《联合国关于危险货物运输的建议书—试验和标准手册 》(ST/SG/AC.10/11/Rev.6) 《United Nations Recommendations On The Transport Of Dangerous Goods, Manual Of Tests And Criteria》(ST/SG/AC.10/11/Rev.6).



Shenzhen Anbotek Compliance Laboratory Limited

Report No. SZABB190109001-01

Page 3 of 17

校准有效期

3. 测试项目 (TEST ITEM)

1. 高度模拟 (Altitude simulation) 5. 外部短路(External short circuit)

2. 温度试验(Thermal test) 6. 撞击(Impact)

3. 振动(Vibration) 7. 过度充电(Overcharge)

4. 冲击(Shock) 8. 强制放电(Forced discharge)

4. 本次检测所使用的设备清单:

wajor instruments of mea	surement used	in the test.
设备名称/型号		
	The second secon	

		D 4 1 1 1 1 1 1 1 1 1 1 1 1 1 1 1 1 1 1
Name of equipment /Model 模拟高空低压试验箱	Serial No.	Due Date
模拟高空低压试验箱 Low Pressure Test Machine		
	SE-132	2019-04-19
Low Pressure Test Machine BE-DY-125 执海沮亦僚		
快速温变箱	Anbotek Anbo	
riigiri ast remperatareariamianty chamber	SE-1488	2019-08-05
ZJ-KSWB1506 振动台		
振动台 Vibration Machine		Vupore V
Vibration Machine EV103V	SE-439	2019-04-09
	ak anbotek	Anbo
かいがれて 山 口		
Gridok Madrinie	SE-440	2019-04-09
HSKT-10		
温控型短路试验机	SE-133	
Thermostat Short-circuit Testing Machine	SE-133	2019-03-29
BE-1000W	aboten Ar	
撞击试验机 Impact Testing Machine BE-5060		
Impact Lecting Machine	SE-136	2019-08-05
Impact Testing Machine BE-5060		
BE-5060 电池充放电系统 Battery Charge And Discharge System		
	SE-172	2019-04-19
CT-3008-25V10A-NA	SE-172	
	SE-1502	2019-08-05
15FB+ 100 AM		
15FB+ 电子秤 Flectronic scale	Ann	
电子秤 Electronic scale	SE-1483	2019-08-05
CHS-D		

地址: 广东省深圳市宝安区西乡街道后瑞第三工业区 A 栋四楼东

Adress: East of 4/F., Building A, Hourui No.3 Industrial Zone, Xixiang Street, Bao'an District, Shenzhen, Guangdong, China



Shenzhen Anbotek Compliance Laboratory Limited

Report No. SZABB190109001-01

Page 4 of 17

5. 检测地点、环境条件

Place and Environmental Conditions of the test

地点:深圳安博检测股份有限公司电池实验室 温度 (20±5) ℃ 相对湿度 (40~70) %RH

Place Temperature R.H.

6. 测试结论(CONCLUSION)

测试项目	样品编号	执行标准	结论
ITEM	SAMPLE NUMBER	STANDARD	CONCLUSION
高度模拟	C1~C10	And stek an	通过 (PASS)
(Altitude simulation)	All hoter	Anbo	otek Anbore
温度试验(Thermal test)	Anbo K A	tek Anbote	通过 (PASS)
振动(Vibration)	Anbote. Anb	tek abotek	通过 (PASS)
冲击(Shock)	k abotek A	ibote K Air	通过 (PASS)
外部短路	ok hotek	UN38.3	通过 (PASS)
(External short circuit)	ofe. Aug	abotek Anbot	通过 (F A33)
撞击(Impact)	C11~C15	All otek Ani	通过 (PASS)
过度充电(Overcharge)	N.A. otek	Ando	botek N.A. Anbote
强制放电	C16~C25 C26~C35	lek Anbore	選升 (DACC)
(Forced discharge)	Aupor All.	otek Anbotek	通过 (PASS)

说明(Notes):

C1~C10:为第一个充放电周期完全充电状态的电芯;

Cells at first cycle in fully charged states;

C11~C15: 为第一个充放电周期 50%设计额定容量状态的电芯;

Cells at first cycle at 50% of the design rated capacity;

C16~C25: 为第一个充放电周期完全放电状态的电芯;

Cells at first cycle in fully discharged states;

C26~C35: 为 50 个充放电周期后完全放电状态的电芯;

Cells after 50 cycles ending in fully discharged states.



深圳安博检测股份有限公司 Shanzhan Anbotak Compliance

Shenzhen Anbotek Compliance Laboratory Limited

Report No. SZABB190109001-01

Page 5 of 17

7. 测试方法 (TEST METHOD)

小型电芯或电池必须按顺序进行试验 T.1 至 T.5。试验 T.6 和 T.8 应使用未另外试验过的电芯或电池。试验 T.7 可以使用原先在试验 T.1 至 T.5 中使用过的未损坏电池进行,以便测试交替充电放电过的电池。

质量损失依照下式计算:

质量损失(%)= (M₁-M₂)/M₁ *100

式中 M1 是实验前的质量,M2 是试验后的质量。如质量损失不超过下表所列数值,即视为"无质量损失"。

Tests T.1 to T.5 shall be conducted in sequence on the same cell or battery. Tests T.6 and T.8 shall be conducted using not otherwise tested cells or batteries. Test T.7 may be conducted using undamaged batteries previously used in tests T.1 to T.5 for purposes of testing on cycled batteries.

In order to quantify the mass loss, the following procedure is provided:

Mass loss(%) = $(M1-M2) / M1 \times 100$

Where M1 is the mass before the test and M2 is the mass after the test. When mass loss does not exceed the values in Table blow, it shall be considered as "no mass loss".

电芯或电池质量 M Mass M of cell or battery	质量损失限值 Mass loss limit
M<1 克(g)	0.5%
1g≤M≤75 克(g)	0.2%
M>75 克(g)	0.1%

T.1 高度模拟

试验电芯和电池应在压力等于或低于 11.6 千帕和环境温度为(20℃±5℃) 下存放至少 6 小时。要求电芯和电池无渗漏、无排气、无解体、无破裂、无起火,并且每个试验电芯或电池在试验后的开路电压不小于其在进行这一实验前电压的 90%。有关电压的要求不适用于完全放电状态的试验电芯和电池。

T.1 Altitude simulation

Test cells and batteries shall be stored at a pressure of 11.6 kPa or less for at least six hours at ambient temperature (20 ± 5 °C).

Cells and batteries meet this requirement if there is no leakage, no venting, no disassembly, no rupture and no fire and if the open circuit voltage of each test cell or battery after testing is not less than 90% of its voltage immediately prior to this procedure. The requirement relating to voltage is not applicable to test cells and batteries at fully discharged states.

T.2 温度试验

试验电芯和电池应先在试验温度等于 75℃±2℃的条件下存放至少 6 小时,接着再在试验温度等于 -40℃±2℃的条件下存放至少 6 小时。两个极端试验温度之间的最大时间间隔为 30 分钟。此程序重复进行,完成 10 次,接着将所有试验电芯和电池在环境温度(20℃±5℃)下存放 24 小时。对于大型电芯和电池,暴露于极端试验温度的时间至少应为 12 小时。

要求电芯和电池无渗漏、无排气、无解体、无破裂和无起火,并且每个试验电芯或电池在试验后的 开路电压不小于其在进行这一试验前电压的 90%。有关电压的要求不适用于完全放电状态的试验电芯和 电池。



深圳安博检测股份有限公司 Shenzhen Anbotek Compliance

Shenzhen Anbotek Compliance Laboratory Limited

Report No. SZABB190109001-01

Page 6 of 17

T.2 Thermal test

Test cells and batteries are to be stored for at least six hours at a test temperature equal to 75 ± 2 °C, followed by storage for at least six hours at a test temperature equal to 40 ± 2 °C. The maximum time interval between test temperature extremes is 30 minutes. This procedure is to be repeated until 10 total cycles are complete, after which all test cells and batteries are to be stored for 24 hours at ambient temperature (20 ± 5 °C). For large cells and batteries the duration of exposure to the test temperature extremes should be at least 12 hours.

Cells and batteries meet this requirement if there is no leakage, no venting, no disassembly, no rupture and no fire and if the open circuit voltage of each test cell or battery after testing is not less than 90% of its voltage immediately prior to this procedure. The requirement relating to voltage is not applicable to test cells and batteries at fully discharged states.

T.3 振动

电芯和电池紧固于振动机平台,但不得造成电芯变形,并能准确可靠地传播振动。振动应是正弦波形,对数扫描频率在 7Hz 和 200Hz 之间,在回到 7Hz,跨度为 15 分钟。这一振动过程须对三个相互垂直的电芯安装方位的每一方向重复进行 12 次,共为时 3 小时。其中一个振动方向必须与端面垂直。

作对数式频率扫描,对总质量不足 12 千克的电芯和电池(电芯和小型电池),和对 12 千克及更大的电池有所不同。

对电芯和小型电池: 从 7Hz 开始,保持 1g 的最大加速度,直到频率达到 18Hz。然后将振幅保持在 0.8mm(总位移 1.6mm),并增加频率直到最大加速度达到 8g(频率约为 50Hz)。将最大加速度保持在 8g 直到频率增加到 200Hz。

对大型电池:从 7 赫兹开始保持 1gn 的峰值加速度直到频率达到 18 赫兹。然后将振幅保持在 0.8 毫米(总行程 1.6 毫米)并增加频率直到最大加速度达到 2gn(频率约为 25 赫兹)。将峰值加速度保持在 2gn 直到频率增加到 200 赫兹。

要求电芯和电池无渗漏、无排气、无解体、无破裂和无起火,并且每个试验电芯或电池在试验后的 开路电压不小于其在进行这一试验前电压的 90%。有关电压的要求不适用于完全放电状态的试验电芯和 电池。

T.3 Vibration

Cells and batteries are firmly secured to the platform of the vibration machine without distorting the cells in such a manner as to faithfully transmit the vibration. The vibration shall be a sinusoidal waveform with a logarithmic sweep between 7 Hz and 200 Hz and back to 7 Hz traversed in 15 minutes. This cycle shall be repeated 12 times for a total of 3 hours for each of three mutually perpendicular mounting positions of the cell. One of the directions of vibration must be perpendicular to the terminal face. The logarithmic frequency sweep shall differ for cells and batteries with a gross mass of not more than 12 kg (cells and small batteries), and for batteries with a gross mass of more than 12 kg (large batteries).

For cells and small batteries: from 7 Hz a peak acceleration of 1 gn is maintained until 18 Hz is reached. The amplitude is then maintained at 0.8 mm (1.6 mm total excursion) and the frequency increased until a peak acceleration of 8 gn occurs (approximately 50 Hz). A peak acceleration of 8 gn is then maintained until the frequency is increased to 200 Hz.

For large batteries: from 7 Hz to a peak acceleration of 1 gn is maintained until 18 Hz is reached. The amplitude is then maintained at 0.8 mm (1.6 mm total excursion) and the frequency increased until a peak acceleration of 2 gn occurs (approximately 25 Hz). A peak acceleration of 2 gn is then maintained until the frequency is increased to 200 Hz.

Cells and batteries meet this requirement if there is no leakage, no venting, no disassembly, no rupture and no fire during the test and after the test and if the open circuit voltage of each test cell or battery



Shenzhen Anbotek Compliance Laboratory Limited

Report No. SZABB190109001-01

Page 7 of 17

directly after testing in its third perpendicular mounting position is not less than 90% of its voltage immediately prior to this procedure. The requirement relating to voltage is not applicable to test cells and batteries at fully discharged states.

T.4 冲击

试验电芯和电池用坚硬支架紧固在试验装置上,支架支撑着每个试验电池的所有安装面。

每个电芯须经受最大加速度 150g 和脉冲持续时间 6 毫秒的半正弦波冲击。另外,大型电芯或许须经受最大加速度 50g 和脉冲持续时间 11 毫秒的半正弦波冲击。

电池须经受半正弦波冲击的峰值加速度取决于电池组的质量。对小型电池的脉冲持续时间为 6 毫秒,对大型电池的脉冲持续时间为 11ms.下面的公式用于计算相应的最小峰值加速度。

每个电芯或电池须在三个相互垂直的安装方位的正方向经受三次冲击,接着再反方向经受三次冲击,总共经受 18 次冲击。

要求电芯和电池无渗漏、无排气、无解体、无破裂和无起火,并且每个试验电芯或电池在试验后的 开路电压不小于其在进行这一试验前电压的 90%。有关电压的要求不适用于完全放电状态的试验电芯和 电池。

T.4 Shock

Test cells and batteries shall be secured to the testing machine by means of a rigid mount which will support all mounting surfaces of each test battery.

Each cell shall be subjected to a half-sine shock of peak acceleration of 150 gn and pulse duration of 6 milliseconds. Alternatively, large cells may be subjected to a half-sine shock of peak acceleration of 50 gn and pulse duration of 11 milliseconds.

Each battery shall be subjected to a half-sine shock of peak acceleration depending on the mass of the battery. The pulse duration shall be 6 milliseconds for small batteries and 11 milliseconds for large batteries. The formulas below are provided to calculate the appropriate minimum peak accelerations.

电池 Battery	最小峰值加速度 Minimum peak acceleration	脉冲持续时间 Pulse duration
小型电池 Small batteries	Acceleration(gn)= $\sqrt{\frac{100850}{\text{mass*}}}$	6 ms
aboten Ande	whichever is smaller	tek botek
大型电池 Large batteries	50 g _n or result of formula $Acceleration(gn) = \sqrt{\frac{30000}{mass*}}$ whichever is smaller	Anbotek 11 ms Anbotek

^{*} Mass is expressed in kilograms.

Each cell or battery shall be subjected to three shocks in the positive direction and to three shocks in the negative direction in each of three mutually perpendicular mounting positions of the cell or battery for a total of 18 shocks.

Cells and batteries meet this requirement if there is no leakage, no venting, no disassembly, no rupture and no fire and if the open circuit voltage of each test cell or battery after testing is not less than 90% of its voltage immediately prior to this procedure. The requirement relating to voltage is not applicable to test cells and batteries at fully discharged states.



Report No. SZABB190109001-01

Page 8 of 17

T.5 外部短路

在一定的时间内加热电芯或电池使其外壳达到 57 ± 4 ° 均匀稳定的温度,温升时间取决于电芯或电池的尺寸和外观,并且被评估和记录。如果这种评估记录不可行,那么小型电芯或电池的暴露时间应至少持续 6 小时,大型电芯或电池应至少持续 12 小时。然后使电芯或电池在 57° ± 4 ° 下经受总外电阻小于 0.1 欧姆的短路条件。

这一短路条件应在电芯或电池外壳温度回到 57℃±4℃后持续至少 1 小时,或者大电池的温度下降至最大温升值的一半并保持低于此温度值。

短路和冷却期间应至少在环境温度下进行。

要求电芯和电池外壳温度不超过 **170**℃, 并且在试验过程中及试验后 **6** 小时内无解体,无破裂,无起火。

T.5 External short circuit

The cell or battery to be tested shall be shall be heated for a period of time necessary to reach a homogeneous stabilized temperature of $57 \pm 4^{\circ}\text{C}$, measured on the external case. This period of time depends on the size and design of the cell or battery and should be assessed and documented. If this assessment is not feasible, the exposure time shall be at least 6 hours for small cells and small batteries, and 12 hours for large cells and large batteries. Then the cell or battery at $57 \pm 4^{\circ}\text{C}$ shall be subjected to one short circuit condition with a total external resistance of less than 0.1 ohm. This short circuit condition is continued for at least one hour after the cell or battery external case temperature has returned to $57 \pm 4^{\circ}\text{C}$, or in the case of the large batteries, has decreased by half of the maximum temperature increase observed during the test and remains below that value. The short circuit and cooling down phases shall be conducted at least at ambient temperature. Cells and batteries meet this requirement if their external temperature does not exceed 170 °C and there is no disassembly, no rupture and no fire during the test and within six hours after the test.

T.6 撞击/挤压

撞击(适用于直径不小于18毫米的圆柱形电芯)

试样电芯或组成电芯放在平坦光滑的表面上,一根 316 型不锈钢棒横放在试样中心,钢棒直径 15.8 毫米±0.1 毫米,长度至少 6 厘米,或电芯最长端的尺度,取二者之长者。将一块 9.1 千克±0.1 千克的重锤从 61±2.5 厘米高处跌落到钢棒和试样交叉处,使用一个几乎没有摩擦的、对落体重锤阻力最小的垂直轨道或管道加以控制。垂直轨道或管道用于引导落锤沿水平支撑表面呈 90 度落下。

接受撞击的试样,纵轴应与平坦表面平行并与横放在试样中心的直径 15.8±0.1 毫米弯曲表面的纵轴垂直。每一试样只经受一次撞击。

T.6 Impact / Crush

Impact (applicable to cylindrical cells greater than 18 mm in diameter)

The sample cell or component cell is to be placed on a flat smooth surface. A 15.8 mm \pm 0.1mm diameter, at least 6 cm long, or the longest dimension of the cell, whichever is greater, Type 316 stainless steel bar is to be placed across the centre of the sample. A 9.1 kg \pm 0.1 kg mass is to be dropped from a height of 61 \pm 2.5 cm at the intersection of the bar and sample in a controlled manner using a near frictionless, vertical sliding track or channel with minimal drag on the falling mass. The vertical track or channel used to guide the falling mass shall be oriented 90 degrees from the horizontal supporting surface.

The test sample is to be impacted with its longitudinal axis parallel to the flat surface and perpendicular to the longitudinal axis of the 15.8 mm \pm 0.1mm diameter curved surface lying across the centre of the test sample. Each sample is to be subjected to only a single impact.



Shenzhen Anbotek Compliance Laboratory Limited

Report No. SZABB190109001-01

Page 9 of 17

挤压 (棱柱形、袋装、硬币/纽扣电芯和直径小于 18 毫米的圆柱形电芯)

将电芯或组成电芯放在两个平面之间挤压,挤压力度逐渐加大,在第一个接触点上的速度大约为 1.5 厘米每秒。挤压持续进行,直到出现以下三种情况之一:

- (a) 施加的力量达到 13KN±0.78KN;
- (b) 电芯的电压下降至少 100mV;
- (c) 电芯变形达到原始厚度的 50%或以上。
- 一旦达到最大压力、电压下降 100mV 或更多,或电芯变形至少达原厚度的 50%,即可解除压力。 棱柱形或袋装电芯应从最宽的一面施压。纽扣/硬币形电芯应从其平坦表面施压。圆柱形电芯应从与纵轴 垂直的方向施压。

每个试样电芯或组成电芯只做一次挤压试验。试样应继续观察 6 小时。试验应使用之间未做过其他 试验的电芯或组成电芯进行。

要求电芯或组成电芯外壳温度不超过 **170**℃, 并且在试验过程中及试验后 **6** 小时内无解体,无起火。

Crush (applicable to prismatic, pouch, coin/button cells and cylindrical cells not more than 18 mm in diameter)

A cell or component cell is to be crushed between two flat surfaces. The crushing is to be gradual with a speed of approximately 1.5 cm/s at the first point of contact. The crushing is to be continued until the first of the three options below is reached.

- (a) The applied force reaches $13 \text{ kN} \pm 0.78 \text{ kN}$;
- (b) The voltage of the cell drops by at least 100 mV; or
- (c) The cell is deformed by 50% or more of its original thickness.

Once the maximum pressure has been obtained, the voltage drops by 100 mV or more, or the cell is deformed by at least 50% of its original thickness, the pressure shall be released.

A prismatic or pouch cell shall be crushed by applying the force to the widest side. A button/coin cell shall be crushed by applying the force on its flat surfaces. For cylindrical cells, the crush force shall be applied perpendicular to the longitudinal axis.

Each test cell or component cell is to be subjected to one crush only. The test sample shall be observed for a further 6 h. The test shall be conducted using test cells or component cells that have not previously been subjected to other tests.

Cells and component cells meet this requirement if their external temperature does not exceed 170 °C and there is no disassembly and no fire during the test and within six hours after this test.

T.7 过度充电

充电电流必须是制造商建议的最大持续充电电流的两倍。试验的最小电压如下:

- (a)制造商建议的充电电压不大于 18V 时,试验的最小电压应是电池最大充电电压的两倍或 22V 两者中的较小者:
 - (b)制造商建议的充电电压大于 18V 时,试验的最小电压应为最大充电电压的 1.2 倍。试验应在环境温度下进行,进行试验的时间应为 24 小时。

要求充电电池在试验过程中和试验后7天内无解体,无起火。

T.7 Overcharge

The charge current shall be twice the manufacturer's recommended maximum continuous charge current. The minimum voltage of the test shall be as follows:

- (a) When the manufacturer's recommended charge voltage is not more than 18V, the minimum voltage of the test shall be the lesser of two times the maximum charge voltage of the battery or 22V.
- (b) When the manufacturer's recommended charge voltage is more than 18V, the minimum voltage of the test shall be 1.2 times the maximum charge voltage.

Tests are to be conducted at ambient temperature; the duration of the test shall be 24 hours.



Shenzhen Anbotek Compliance Laboratory Limited

Report No. SZABB190109001-01

Page 10 of 17

Rechargeable batteries meet this requirement if there is no disassembly and no fire during the test and within seven days after the test.

T.8 强制放电

每个电芯应在环境温度下与 12V 直流电电源串联在起始电流等于制造商给定的最大放电电流的条件下强制放电。

将适当大小和额定值的电阻负荷与试验电池串联,计算得出给定的放电电流。对每个电池进行强制 放电,放电时间应等于其额定容量除以初始试验电流。

要求原电芯或充电电芯在试验过程中和试验后7天内无解体,无起火。

T.8 Forced discharge

Each cell shall be forced discharged at ambient temperature by connecting it in series with a 12V D.C. power supply at an initial current equal to the maximum discharge current specified by the manufacturer. The specified discharge current is to be obtained by connecting a resistive load of the appropriate size and rating in series with the test cell. Each cell shall be forced discharged for a time interval (in hours) equal to its rated capacity divided by the initial test current (in ampere).

Primary or rechargeable cells meet this requirement if there is no disassembly and no fire during the test and within seven days after the test.




Shenzhen Anbotek Compliance Laboratory Limited

Report No. SZABB190109001-01

Page 11 of 17







Report No. SZABB190109001-01

Page 12 of 17

9. 测试数据 DATA

T.1 高度模拟(Altitude simulation)

电池	测试前	Pre-test	测试后。	After test	质量亏损	电压亏损	有无渗漏,排气,解
编号	质量	电压	质量	电压	Mass loss	Voltage	体,破裂和起火(是
No.	Mass	Voltage	Mass	Voltage	(%)	loss (%)	/否)
YOK	克(g)	伏(V)	克(g)	伏(V)		00,	Whether leakage,
Anbou	b.	otek	Anboten	Anbe		Anbotek	venting, disassembly, rupture, fire (Y/N)
C1	39.512	3.438	39.512	3.438	0.00	0.00	Non.
C2	39.474	3.453	39.474	3.453	0.00	0.00	N vek
C3 no	39.402	3.418	39.402	3.417	0.00	0.03	er Noos
C4	39.373	3.432	39.368	3.432	0.01	0.00	N self
C5	39.525	3.426	39.525	3.426	0.00	0.00	otek Nanbo
C6	39.486	3.473	39.486	3.473	0.00	0.00	N N
C7	39.768	3.435	39.768	3.434	0.00	0.03	noter N Anbo
C8	39.764	3.447	39.759	3.447	0.01	0.00	Ann N
C9	39.471	3.462	39.471	3.462	0.00	0.00	hoteN And
C10	39.787	3.451	39.787	3.451	0.00	0.00	And N

T.2 温度测试(Thermal test)

测试前	Pre-test	测试后。	After test	质量亏损	电压亏损	有无渗漏,排气,解
质量	电压	质量	电压	Mass loss	Voltage	体,破裂和起火(是
Mass	Voltage	Mass	Voltage	(%)	loss (%)	/否)
克(g)	伏(V)	克(g)	伏(V)	./	oter	Whether leakage,
Anbo	tek	nbotek	Anbore	V. Vur	hotek	venting, disassembly, rupture, fire (Y/N)
39.512	3.438	39.498	3.425	0.04	0.38	N ^N
39.474	3.453	39.459	3.439	0.04	0.41	And N
39.402	3.417	39.385	3.404	0.04	0.38	k Noter
39.368	3.432	39.353	3.418	0.04	0.41	PN
39.525	3.426	39.509	3.414	0.04	0.35	N noter
39.486	3.473	39.472	3.459	0.04	0.40	ore Name
39.768	3.434	39.753	3.421	0.04	0.38	K N Pofe,
39.759	3.447	39.745	3.435	0.04	0.35	abore N Am
39.471	3.462	39.456	3.448	0.04	0.40	LekN bo
39.787	3.451	39.771	3.437	0.04	0.41	Vupor N V
	质量 Mass 克(g) 39.512 39.474 39.402 39.368 39.525 39.486 39.768 39.759 39.471	Mass 克(g) Voltage 伏(V) 39.512 3.438 39.474 3.453 39.402 3.417 39.368 3.432 39.525 3.426 39.486 3.473 39.768 3.434 39.759 3.447 39.471 3.462	所量 电压 所量 Mass 克(g) Voltage	所量 电压 所量 地压 Voltage 穴(g) 欠(V) 欠(V) 欠(V) 欠(V) 欠(V) 欠(V) 欠(V) 欠(V	横量 电压	展量 电压 Mass Voltage 大(V) 名の Voltage Voltage 大(V) 名の 大(V) 日本 Voltage 大(V) 大(V) 日本 Voltage 大(V) Voltage Toltage Toltag



Report No. SZABB190109001-01

Page 13 of 17

T.3 振动(Vibration)

	2.10					10.00
测试前	Pre-test	测试后。	After test	质量亏损	电压亏损	有无渗漏,排气,解
质量	电压	质量	电压	Mass loss	Voltage	体,破裂和起火(是
Mass	Voltage	Mass	Voltage	(%)	loss (%)	/否)
克(g)	伏(V)	克(g)	伏(V)		You	Whether leakage,
20018		0	n te		ore	venting, disassembly,
Ans	36	tek	Vupo	Z.	You	rupture, fire (Y/N)
39.498	3.425	39.498	3.425	0.00	0.00	A ^{tt} N _{-X}
39.459	3.439	39.456	3.439	0.01	0.00	N. S.
39.385	3.404	39.385	3.404	0.00	0.00	An N
39.353	3.418	39.353	3.418	0.00	0.00	ex Noore
39.509	3.414	39.509	3.413	0.00	0.03	N water
39.472	3.459	39.472	3.459	0.00	0.00	Tek N NDOLO
39.753	3.421	39.753	3.421	0.00	0.00	N P
39.745	3.435	39.745	3.434	0.00	0.03	stek N anbor
39.456	3.448	39.452	3.448	0.01	0.00	Aupo N
39.771	3.437	39.771	3.437	0.00	0.00	ateN not
	所量 Mass 克(g) 39.498 39.459 39.385 39.353 39.509 39.472 39.753 39.745 39.456	Mass 克(g) Voltage 伏(V) 39.498 3.425 39.459 3.439 39.385 3.404 39.353 3.418 39.509 3.414 39.472 3.459 39.753 3.421 39.745 3.435 39.456 3.448	所量 电压 所量 Mass 克(g) Voltage 代(V) 名9.498 3.425 39.498 39.456 39.385 3.404 39.385 39.509 3.414 39.509 39.472 39.753 39.745 39.456 39.456 39.456 39.456 39.456 39.456 39.456 3.448 39.452	所量 电压 所量 地压 Voltage 穴(g) 欠(V) タリン	所量 电压 所量 地压 (%) Mass loss (%) 対	展量 电压 K(V) Mass Voltage (%) Voltage loss (%) (%) Mass Voltage (%) (%) Mass Voltage (%) Voltage (%)

T.4 冲击(Shock)

峰值加速度: 150 gn, 脉冲时间: 6 ms

Peak acceleration: 150 gn, Pulse duration: 6 ms

电池	测试前 P	Pre-test	测试后 A	After test	质量亏损	电压亏损		气,解
编号	质量	电压	质量	电压	Mass loss	Voltage	体,破裂和起	火(是
No.	Mass	Voltage	Mass	Voltage	(%)	loss (%)	/否)	npo
AUDO	克(g)	伏(V)	克(g)	伏(V)	Yo.	hotek	Whether lea	ıkage,
Anbot	Anb	tek	hotek	Anb	ofe. b	in botek	venting, disas rupture, fire	
C1	39.498	3.425	39.498	3.425	0.00	0.00	N	CK
C2	39.456	3.439	39.456	3.439	0.00	0.00	N	A100
C3	39.385	3.404	39.381	3.404	0.01	0.00	N	- Otek
C4	39.353	3.418	39.353	3.417	0.00	0.03	oter Nar	/b-
C5	39.509	3.413	39.509	3.413	0.00	0.00	N N	"Ofek
C6	39.472	3.459	39.472	3.459	0.00	0.00	-pote, N	AUD
C7	39.753	3.421	39.753	3.421	0.00	0.00	_{-K} N	20
C8	39.745	3.434	39.745	3.434	0.00	0.00	N Storber	VUP
C9	39.452	3.448	39.447	3.448	0.01	0.00	N. N.	
C10	39.771	3.437	39.771	3.436	0.00	0.03	Noon	V.



Report No. SZABB190109001-01

Page 14 of 17

T.5 外部短路(External short circuit)

D/1.	16.	7
电池编号 No.	最高温度	有无解体,破裂,起火(是/否)
er Anbe	Peak temperature (°C)	Whether disassembly, rupture, fire (Y/N)
C1 Ctek	78.2	Lek boter NAME
C2 (TV	81.5	Ande N hoter Ande
C3 hoten	77.6	tek above N Ame
C4	79.2	upo An Hote An
C5 001	82.3	atek anbor N All ak
C6	75.4	Anbe Nx nbote
C7	77.3	otek PupoN
C8	76.9	And Natek about
C9	81.7	hotel AN
C10	79.8	And I N otek Anbot

T.6 撞击(Impact)

电池编号 No.	最高温度	有无解体,起火(是/否)
anbore Ant	Peak temperature (°C)	Whether disassembly, fire (Y/N)
C11	87.5	Stek MooN W
C12	89.2	And Neek about
C13	88.6	otek MNO K. Lek
C14	90.7	And N stek support
C15	89.8	ok hotel Nabo

T.7 过度充电(Overcharge)

电池编号 No.		无解体,起火(是/		Ken. V
All Lok	Whe	ether disassembly, fire	(Y/N)	
N.A.	. K hotek	N.A.	49.4	, boto.
N.A.	above And	N.A.	Aupor Ai	You
N.A.	ak hotek	N.A.	" KEK	Sporte
N.A.	Spore Aug	N.A.	Vupos	V.
N.A.	A. Pote,	N.A.	tek	hoto
N.A.	Whole Mur	N.A.	Anbo	Α.
N.A. Mb	A. bo	N.A.	rek	nbo
N.A.	A upor	N.A.	er Anbo	W.



Report No. SZABB190109001-01

Page 15 of 17

T.8 强制放电(Forced discharge)

37	电池编号 No.	Vupose	Dur	有无解	体,起火	(是/否)	0,	-tek	
Cer	Anbo	Whether disassembly, fire (Y/N)							
\	C16	Aupo	N.	*eK	No	P	'Up.	250	
100te	C17	, as	ek	upor	N	No.	hoter	Anbe	
	C18 Noter	Aupo	P	Yek	N	poro	VUL	V	
da	C19 A	VC.	-otek	Aupo	N	*eK	Jodge Williams	Yu,	
Pr.	C20	V. Vu	6	10	ek N	Aupor	511.	You	
	nb ⁰ C21	40.	hoten	AUDO	N	46/	100	Poto	
Y	C22	Octo	VII.		ote N	Aupo	12.	Yo.K	
	C23	494	abolie.	VU.	N .	,	tek	Mpor	
V	C24	VUpor	Dr.	n/K	No.	VUD.	·	rek	
18,	C25	-10K	100	200	Pur. N	.V.	Lotek	Aupo	
V	C26	Anbo	pe	*eK	Not	P	Up	o'te	
00/6	C27		sk v	upor	N	You	hoter	Aupo	
	C28	AUD		rek	N _s	POLO	VIII	V. W	
npc	C29	K v	oter	Aupo	N	rek	Sporte	AUR	
15.	C30	An	D	010	s _K N	Vupor	Dr.	You	
100	C31	You	pole.	Aup	N	-kek	dn	or b	
1	C32	,010	VII.		ote N	VUPO	γ.	*eK	
	Anio C33	*eV	"pote.	VU.	N _v		tek .	nboc	
M	C34	upor	br.	You	NoN"	Aup	1	Yek	
Sec	C35	1ek	2000	10	N. N	K	"Ofek	AUPO	
		WV	1/4		2.5	7			



Report No. SZABB190109001-01

Page 16 of 17

10. 样品照片(Photos of the Sample)

电芯(Cell)







Report No. SZABB190109001-01

Page 17 of 17

声明 (DECLARATION)

1. 测试参考文件:《联合国关于危险货物运输的建议书一试验和标准手册》 (ST/SG/AC.10/11/Rev.6)

《United Nations Recommendations On The Transport Of Dangerous Goods, Manual Of Tests And Criteria》(ST/SG/AC.10/11/Rev.6).

2. 测试实验室: 深圳安博检测股份有限公司

地址:广东省深圳市宝安区西乡街道后瑞第三工业区A栋四楼东

Test place Lab: Shenzhen Anbotek Compliance Laboratory Limited

Address: East of 4/F., Building A, Hourui No.3 Industrial Zone, Xixiang Street, Bao'an District, Shenzhen, Guangdong, China

3. 本报告不能修改和删除。

This report shall not be revised and deleted.

4. 本报告出现的试验结果仅与试验样品有关。

The test results presented in this report are only relevant to the test sample.

- 5. 本报告在未经深圳安博检测股份有限公司书面许可情况下不能用于宣传、广告之用。
 This report shall not be published as advertisement without the approval of Shenzhen Anbotek Compliance Laboratory Limited.
- 6. 除非全部复制,否则无深圳安博检测股份有限公司书面批准本报告不得部分复制。

This report shall not be copied partly without the written approval of Shenzhen Anbotek Compliance Laboratory Limited.