

RENOLIN B PLUS

High-quality AW/EP hydraulic fluids and lubricating oils formulated on hydrotreated base oils

Description

RENOLIN B PLUS is based on selected, so-called hydrotreated base oils (group II) of the latest generation. Defined additives and additive systems improve the ageing and oxidation stability. They also guarantee excellent corrosion protection for steel and iron materials. Synergistically acting copper inhibitors protect copper and yellow metal materials against corrosion. Selected AW (antiwear) and highly resistant EP (extreme pressure) additives based on zinc containing additive systems protect hydraulic pumps, motors and components and machine elements reliably from wear. This excellent wear protection is guaranteed at high load, high and low temperature and rough environmental conditions.


RENOLIN B PLUS is a premium hydraulic fluid which fulfills and surpasses the requirements defined in DIN 51524-2 (HLP/HM, demulsifying, zinc-containing). RENOLIN B PLUS can also be used as lubrication and circulating oil.

By using these new high-quality base oils, the lifetime extension compared to conventional hydraulic fluids is extraordinary. Lifetime can be doubled – compared to group I (standard mineral oil) based hydraulic fluids.

Due to the excellent thermal oxidation stability the product shows extremely low deposit tendency (Low Varnish Fluid). RENOLIN B PLUS series shows excellent air release properties – low air enrichment and rapid dynamic air separation.

Advantages

- High-quality base oils of the latest generation
- Excellent demulsifying properties
- Very good corrosion protection - steel
- Excellent corrosion protection - copper
- High ageing and oxidation stability (extended lifetime)
- Good AW/EP wear protection
- Very good hydrolytic stability
- Excellent filtration behaviour (dry and under influence of water)
- Excellent foaming behaviour – no surface foam
- Excellent air release (ISO VG 46: 4 minutes!)
- Premium hydraulic fluid



PI 4-1533, Page 1; PM 4 / 10.21

RENOLIN B PLUS

High-quality AW/EP hydraulic fluids and lubricating oils formulated on hydrotreated base oils

Application

Universally applicable demulsifying hydraulic fluid and lubrication oil (for circulating and bearing lubrication). Suitable for all applications in mobile and stationary hydraulic equipment / hydraulic components, for which the use of a demulsifying hydraulic oil (good water separation), type HLP/HM, is mandatory. Synergistically acting additives guarantee a long life time and highest hydraulic performance and good power transfer. Also at high temperature and high pressures the synergistically acting properties of base oils and additive technology guarantee a reliable operation of the equipment components and machines, long lifetime, increased service interval, double to triple life.

RENOLIN B PLUS has excellent thermal, oxidative and hydrolytic stability. The formation of hydrolysis products under water contamination is avoided.

RENOLIN B PLUS shows excellent filtration behaviour in the dry and wet filtration procedure.

RENOLIN B PLUS shows excellent wear protection properties also at high load and high temperature.

RENOLIN B PLUS guarantees rapid air release properties – also at high circulation rate.

Specifications

RENOLIN B PLUS fulfils and surpasses the requirements according to:

- DIN 51524-2: HLP
- ISO 6743-4: HM
- Vickers vane pump

Approvals

- Bosch Rexroth RDE 90245
(ISO VG 32 / 46 / 68)
- DENISON HF-0
(ISO VG 32 / 46 / 68)

RENOLIN B PLUS

High-quality AW/EP hydraulic fluids and lubricating oils formulated on hydrotreated base oils

Typical data:

		RENOLIN B PLUS				
Product name		10	15	22	32	
Properties	Unit					Test method
ISO VG		10	15	22	32	DIN 51519
Kinematic viscosity at 40 °C	mm²/s	10	15	22	32	DIN EN ISO 3104
at 100 °C	mm²/s	2.7	3.5	4.4	5.5	
Viscosity index	-	104	108	108	108	DIN ISO 2909
Density at 15 °C	kg/m³	840	840	845	862	DIN 51757
Color	ASTM	0.5	0.5	0.5	0.5	DIN ISO 2049
Flash point in open cup acc. to Cleveland	°C	170	195	220	220	DIN ISO 2592
Pourpoint	°C	-54	-48	-45	-39	DIN ISO 3016
Neutralization number	mgKOH/g	0.5	0.5	0.5	0.5	DIN 51558-3
Air release properties	min	1	1	2	3	DIN ISO 9120
Copper corrosion (type value)	degree of corrosion	1-100A3				DIN EN ISO 2160
Steel corrosion (type value)						DIN ISO 7120
- 0-A: distilled water	-	no rust				
- 0-B: salt water	-	no rust				
Scuffing and scoring test, FZG A/8.3/90	failure load stage	-	-	10	11	DIN ISO 14635-1
Vickers V104C vane pump						DIN EN ISO 20763
- Wear of pump ring	mg	-	-	-	30	
- Wear of vanes	mg	-	-	-	2	
Brugger-Test (type value)	N/mm²	25				DIN 51347-2
TOST Lifetime (type value)	h	> 5,000				ASTM D 943
Electric conductivity at 75 °C		conductivity high				ASTM D 2624

RENOLIN B PLUS

High-quality AW/EP hydraulic fluids and lubricating oils formulated on hydrotreated base oils

Typical data:

RENOLIN B PLUS					
Product name		46	68	100	
Properties	Unit				Test method
ISO VG		46	68	100	DIN 51519
Kinematic viscosity at 40 °C	mm ² /s	46	68	100	DIN EN ISO 3104
at 100 °C	mm ² /s	6.94	9.0	11.6	
Viscosity index	-	107	108	104	DIN ISO 2909
Density at 15 °C	kg/m ³	865	867	870	DIN 51757
Color	ASTM	0.5	0.5	0.5	DIN ISO 2049
Flash point in open cup acc. to Cleveland	°C	230	230	270	DIN ISO 2592
Pourpoint	°C	-36	-33	-33	DIN ISO 3016
Neutralization number	mg/KOH/g	0.5	0.5	0.5	DIN 51558-3
Air release properties	min	4	6	7	DIN ISO 9120
Copper corrosion (type value)	degree of corrosion		1-100A3		DIN EN ISO 2160
Steel corrosion (type value)					DIN ISO 7120
- 0-A: distilled water	-		no rust		
- 0-B: salt water	-		no rust		
Scuffing and scoring test, FZG A/8.3/90	failure load stage		11		DIN ISO 14635-1
Vickers V104C vane pump					DIN 51389-2
- Wear of pump ring	mg	30	30	30	
- Wear of vanes	mg	2	2	2	
Brugger-Test (type value)	N/mm ²		25		DIN 51347-2
TOST Lifetime (type value)	h		> 5,000		ASTM D 943
Electric conductivity at 75 °C			conductivity high		ASTM D 2624