

TEROSON® WX 215

January 2022

PRODUCT DESCRIPTION

TEROSON® WX 215 provides the following product characteristics:

Technology	Anti-corrosion compound
Chemical Type	Wax, anti-rust additive
Appearance	Light brown
Components	One component - requires no mixing
Viscosity	Liquid
Cure	Not applicable
Application	Anti-corrosion for cavity protection
Application Temperature	15 to 25°C (59 to 77 °F)
In service temperature	-40 to 90°C (-40 to 194 °F)
Short exposure (up to 1h)	100°C (212 °F)
Specific Benefits	• Excellent penetration and climb ability • Good temperature resistance

TEROSON® WX 215 is a solvent-based anti-corrosion agent for the protection of cavities. It is a thin, slightly thixotropic, atomizing spray which can reach narrow spaces using the spray tube clung to the cap. Spray creeps into gaps and drives out moisture. The product contains a high proportion of rust inhibitors. Teroson® WX 215 has outstanding creep qualities, penetrates well into the spaces to be protected (e.g. welds). The material can even be used at temperatures as low as 10°C (50°F), though creep qualities are improved if the product and the bodywork are at room temperature. When fully dry, the anti-corrosion agent forms a soft remaining, water-repellent film of a light brown, nearly translucent colour.

TEROSON® WX 215 is used in workshops principally for spraying the open interiors of cavities as an additional protection over and above the existing cavity sealant in new vehicles and for re-treatment after accident repairs. With the attached spraying head the anti-corrosion agent can also be sprayed for the protection of areas, e.g. on underbodies resulting in a high rust protection and a fresh, new appearance.

TYPICAL PROPERTIES

Specific Gravity @23°C	0.72
Drop point of solid, DIN 51801, °C	60
Solids, %	40
Salt spray, DIN 50021, hours	240
Sag resistance, µm	100
Penetration, mm	20
Paint drying, 1.5 hours @60°C	No running
Corrosion resistance, D50021, 35°C, salt solution 5%, 240 hours, dry film resistance 50 µm	No corrosion

GENERAL INFORMATION

This product is not recommended for use in pure oxygen and/or oxygen rich systems and should not be selected as a sealant for chlorine or other strong oxidizing materials.

For safe handling information on this product, consult the Safety Data Sheet (SDS).

Use only in a well ventilated area.

Direction for use

Surface preparation

1. Any items of trim and covers should be removed. Any rust should be removed as far as possible.
2. To spray awkward areas (e.g. semi-hollow zones such as doors etc.), the special spray head with the tube is used. The material should be at room temperature when used.
3. If stored for long periods and if the material is at a temperature below 15°C, the material becomes more thixotropic.

Application

1. The can should be shaken vigorously before use until the ball-bearing becomes audible.
2. The body parts should be sprayed evenly, with the can held upright during spraying.
3. When using the spray tube, this can be moved slowly in circles whilst spraying so that all directions are covered.
4. The spray head with the circular jet nozzle enables fine and even coating of areas, e.g. on the vehicle underbody, resulting in an excellent appearance.
5. Slightly spraying rubber and plastic parts makes these look clearly fresher.

Cleaning



1. Any escaping TEROSON® WX 215 can be wiped off easily. mPa·s = cP
2. TEROSON® WX 215 is suitable for cleaning partially dried material.
3. Any splashes onto painted surfaces should be removed immediately.

Handling Precautions

Product must be handled in a manner applicable to highly flammable materials and in compliance with relevant local regulations. The solvent can affect certain plastics or coatings. It is recommended to check all surfaces for compatibility before use.

Storage

Store product in the unopened container in a dry location. Storage information may also be indicated on the product container labelling.

Optimal Storage: 15 to 25 °C. Storage below 15 °C or greater than 25 °C can adversely affect product properties.

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Henkel representative.

Product Specification

The technical data contained herein are intended as reference only and are not considered specifications for the product. Product specifications are located on the Certificate of Analysis or please contact Henkel representative.

Approval and Certificate

Please contact Henkel representative for related approval or certificate of this product.

Data Ranges

The data contained herein may be reported as a typical value. Values are based on actual test data and are verified on a periodic basis.

Temperature/Humidity Ranges: 23 °C / 50% RH = 23±2 °C / 50±5% RH

Conversions

$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$

$\text{kV/mm} \times 25.4 = \text{V/mil}$

$\text{mm} / 25.4 = \text{inches}$

$\mu\text{m} / 25.4 = \text{mil}$

$\text{N} \times 0.225 = \text{lb}$

$\text{N/mm} \times 5.71 = \text{lb/in}$

$\text{N/mm}^2 \times 145 = \text{psi}$

$\text{MPa} \times 145 = \text{psi}$

$\text{N}\cdot\text{m} \times 8.851 = \text{lb}\cdot\text{in}$

$\text{N}\cdot\text{m} \times 0.738 = \text{lb}\cdot\text{ft}$

$\text{N}\cdot\text{mm} \times 0.142 = \text{oz}\cdot\text{in}$



Disclaimer

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation or Henkel Canada, Inc. the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 0.0

