

650 NZA MAT

GALVANIZATION – ANTICORROSION

ALONG WITH

SALT SPRAY RESISTANCE > 500 HOURS

BENEFITS

- Quick drying.
- Can be covered with any paint.
- Passivation of the surface which continues and is reinforced over time by the formation of a ferro-zinc alloy on the surface.
- Formulation based on lamellar zinc.
- Excellent resistance to chemicals (except acids), weathering and corrosion.

- Good adhesion to steel.
- Safe compared to butane-propelled “bombs”.
- Covering power greater than “galva butane”, approximately +30% active product.



DEFINITION

Anti-rust coating, with a very high zinc content, for the protection by cold galvanization of all metal parts subjected to saline, corrosive, bad weather, etc. environments.

INSTRUCTIONS FOR USE

Remove all detachable parts of the metal: powdery rust, scale, grease.

Aerosol: shake vigorously, the balls should roll freely.

Spray from about 20 cm regularly, avoiding dripping.

Quickly drain the aerosol upside down after use.

Propellant GAS: non-flammable = CO₂.

FEATURES

| | |
|--------------------------|-----------------------------|
| Appearance after drying: | Along with |
| Color : | Gray |
| Density (NFT 60-101): | ~ 1,03 |
| Dust-free drying time: | Instant |
| Salt spray resistance: | > 500 h |
| Covering power: % in | 1.5 m ² /aerosol |
| Metal: | > 62.65% of dry film |
| Zinc purity: | > 99 % |

ORAPI® cannot be aware of all the applications in which its products are used and the conditions of their use. ORAPI® assumes no responsibility for: the suitability of its products for a given use or for a particular purpose, the application methods over which it has no control. The information contained in this technical data sheet must in no case replace the preliminary tests that must be carried out to verify the suitability of the product for each intended application. The user of the product described in this technical data sheet remains solely responsible for all measures required to protect people and property against all risks that may result from the implementation and/or use of this product. Consequently, ORAPI® disclaims all implied or explicit warranties, including warranties relating to the fitness for sale or suitability for a particular need, resulting from the sale or use of its products. ORAPI® specifically denies any prosecution for incidental or consequential damages of any kind, including financial operating losses.



650 NZA MAT

GALVANIZATION – ANTICORROSION

ALONG WITH

SALT SPRAY RESISTANCE > 500 HOURS

FIELD OF APPLICATION

Rails, highway guardrails, welding bead connections on galvanized parts, frames and agricultural equipment.

Wire mesh, barriers, pipes, tanks and any metal support requiring galvanization protection.

Any metal surface (iron, steel, galvanized and light alloys) particularly exposed to saline, marine and corrosive atmospheres.

PACKAGING

Aerosol 650 ml

ref. 4650A4

x 12



ORAPI® cannot be aware of all the applications in which its products are used and the conditions of their use. ORAPI® assumes no responsibility for: the suitability of its products for a given use or for a particular purpose, the application methods over which it has no control. The information contained in this technical data sheet must in no case replace the preliminary tests that must be carried out to verify the suitability of the product for each intended application. The user of the product described in this technical data sheet remains solely responsible for all measures required to protect people and property against all risks that may result from the implementation and/or use of this product. Consequently, ORAPI® disclaims all implied or explicit warranties, including warranties relating to the fitness for sale or suitability for a particular need, resulting from the sale or use of its products. ORAPI® specifically denies any prosecution for incidental or consequential damages of any kind, including financial operating losses.