

Product: **EPT-Sealer EC-1200N series**


Product group: **Sealing Materials**

## General description


EPT-Sealer EC-1200N is a low emission semi-closed cell EPDM foam with excellent sealing properties. The semi-closed cell structure combines the flexibility of open cell types with the excellent sealing capabilities of closed cell types (after compression).

This unique foam can be laminated with Nitto's advanced adhesive technology to seal (complex) gaps against water, wind, dust, noise and heat.

## Construction



**EC-1200N**  
- Semi-closed EPDM foam



**General purpose**

**EC-1210N**  
- semi-closed EPDM foam (EC-1200N)  
- Acrylic-based adhesive  
- Non-woven carrier  
- Acrylic-based adhesive  
- Release liner



**EC-1250N**  
- semi-closed EPDM foam (EC-1200N)  
- Acrylic-based adhesive  
- Non-woven carrier  
- Acrylic-based adhesive  
- Release liner

**High-end tape 5015ELE for LSE (Low Surface Energy)**  
5015ELE available on separate data sheet

## Characteristics

- The semi-closed EPDM foam EC-1200N meets the low emission standards DIN 75201, VDA 270 VDA 275 and VDA 277.
- EC-1250N is approved by Ford according to odour test standard FLTM BO 131-03.
- Resistance to UV, humidity, high and low temperatures.
- The flexibility of the foam makes sure that the optimal sealing performance is obtained, even with expansion or contraction of the structure caused by temperature changes.
- Due to the low compression load, the foam can compensate dimensional deviations in substrates and avoids in common use deformation of the structure after application.
- Combined with Nitto's advanced adhesive technology, the foam can be applied on rough, smooth and low energy surfaces. Depending on the type of substrate, different adhesives are available in combination with the EPDM foam.
- No heavy metals (such as Cd, Pb, Hg, Cr6) and no regulated substances (such as CFC's and halogen gases) are used during the manufacturing process nor in the product itself. These products comply with the RoHS and ELV directives. IMDS declarations are available upon request.

## Application

EPT-Sealer EC-1200N is especially designed to seal (complex) gaps against water, wind, dust, noise and heat. Depending on the applications, the foam needs to be compressed minimum 70% to activate its sealing properties.

**AUTOMOTIVE** – sealing of HVAC unit, dashboard, air duct, fire wall, all kinds of interior applications which require low emission and low smell.

## Features

- low emission (fogging, VOC, smell, formaldehyde)
- semi-closed cell structure
- super soft / conformable
- low compression load
- good compression set
- ozone resistance
- good weatherability
- fungus free
- excellent ageing performance (dimensional heat stability)
- excellent acoustic performance
- good water sealing

Properties

Foam	Typical Value	Test Method
Thickness	5 to 30 mm*	ISO 1923
Density	90 kg/m <sup>3</sup>	ISO 845
Elongation MD**	170 %	JIS K 6767
Tensile strength MD	48 kPa	JIS K 6767
50% Compression load	4 kPa	Nitto Belgium test method
Compression set	72h, 23 °C = 4% / 22h, 70 °C = 10%	ISO 1856
Watertightness (70%)	no leakage	Nitto Belgium U-shape method***
Acoustic performance	excellent	Nitto Belgium test method
Fogging	1.5 mg	DIN 75201
Formaldehyde emission	0.1 mg/kg	VDA 275
Volatile Organic Components	10 µg C/g	VDA 277
Smell	2 - 3	VDA 270
Adhesion on BA steel at 180° (tape)	min. 700 cN/20 mm	EN 1939

\* thicker material available on request

\*\*\*  Watertightness

\*\* MD = Machine Direction

Complex	Typical Value	Test Method
Adhesion on 2B steel at 90°	min. 400 cN/20 mm	JIS Z 0237
Flammability (ref. 10 mm) for other thicknesses refer to customer product specification	< 100 mm/min.	FMVSS 302
Watertightness (60%)	no leakage	Nitto Belgium U-shape method***
Temperature resistance (dimensional stability)	General -40 to 135 °C In case of extreme temperatures, we recommend to perform application tests.	
Chemical resistance Test solution: acid (1%H <sub>2</sub> SO <sub>4</sub> ) alkaline (1%NaOH), test performed on tensile strength and elongation acc. to JIS K6767	stable	Immersion at 20 °C for 7 days
Ozone resistance Test conditions: 75 ppm ozone, 40 °C, 30 days, 20% elongated sample	no cracks	Visual inspection
Temperature range	-40 °C up to 135 °C	

Warranty

The product is guaranteed to be free from defect in material and workmanship at the time of delivery and will be suitable for use for a period of 6 months thereafter, subject to the conditions set out herein.

Availability

Standard thickness: 5mm, 6mm, 8mm, 10mm, 12mm, 15mm, 18mm, 20mm, 25mm and 30mm

Rolls: widths: 250 mm, 330 mm, 500 mm, 1000 mm & lengths: 10 to 50 m depending on the thickness

Sheets: 1000 mm x 2 m

Application guidelines

- The performance of Nitto EPT-Sealer on specific substrate must be assured by the user before implementation.
- During storage and transport, do not over stack the product, as this may cause deformation.
- EPT-Sealer should be applied to clean and dry surface. Remove excess oil, moisture and dirt from the substrate surface to which the sheet is applied.
- In order to avoid entrapped air-bubbles, tension and shear, the customer should determine appropriate application conditions. The best application conditions are obtained at a temperature between 15 °C and 40 °C.
- Appropriate compression is needed to have sealing performance.
- In case of use of primer, check beforehand the impact of the primer to the performance of the EPT-Sealer. Wrong use of primer can lead to loss of adhesion.
- Please consult Nitto Europe for any robotic application regarding more specific precautions.
- Thickness as referred in orders, article description and on the packaging is related to the foam and is excluding tape and release liner thickness.

If you require additional information on technical properties and application as well as product sampling or testing, please contact your local Nitto sales office.

General conditions of use and precautions:

The properties of the product might be adversely affected by various elements such as composition, condition and surface of and impurities in or on the substrate, temperature and humidity during storage, the surrounding environment at and after application and time of exterior use. When the product is used in combination with another material or process, the user shall assure the compatibility of the product in such combination and whether this combination results in the expected performance. The same principle applies in the event of product use in extreme conditions or circumstances, whether at or after the moment of application, including extended exposure to sunlight or extreme temperatures and pressure.

Packaging, transport and storage:

During transport and storage the product should always be protected against direct sunlight and extremes in temperature and humidity and contained in its original packaging. Once removed from its packaging, it should be promptly applied and remain shielded from direct sunlight and extreme temperature as well as protected against dust and other impurities.

Liability:

Except for its wilful misconduct, Nitto Belgium's liability shall be limited to a replacement, a reimbursement or an additional delivery of the product, and shall not exceed the purchase price of the products. In no event shall Nitto be liable in respect of any indirect or consequential damages, including loss of profits.

The above limitations of liability shall equally apply if Nitto Belgium has assisted in any manner with the selection, treatment or application of the product.

Product information:

This datasheet provides a general description of the product properties and application scope. Full technical details in connection with this product are presented in the customer product specification, which is available upon request.

The information reflected in this datasheet is subject to change and the product described herein may be modified or discontinued without notice.

Edition: January 2019  
Code: DS/05.09/ EC1200N series ENG  
This datasheet replaces all previous versions

Nitto Belgium NV has obtained following certificates:

- ISO 9001
  - ISO 14001
  - IATF 16949
- Please check our website for applicable scope



For your local Nitto sales office, please visit our web site:  
[www.nitto.com](http://www.nitto.com)

Copyright © 2019 NITTO BELGIUM NV. All rights reserved.