

## Description

The 8617 *Super Thermal Grease III* is a low thermal resistance, non-corrosive grease. It uses an extremely thermal stable synthetic oil that is electrically insulating. It is used to improve the thermal interface contact conductivity between heat sinks, LEDs, motors, and heat-generating electronic components such as CPUs, GPU chipsets, and power components. This grease improves the thermal interface between irregular and pitted surfaces.

## Benefits & Features

- **Silicone and ZnO free**
- **High thermal conductivity**
- **Lowers the contact resistance between irregular surfaces**
- **Extends the life of electronic components**
- **Electrically insulating**
- **Non-bleeding**
- **Safe on plastics**

## Usage Parameters

<i>Properties</i>	<i>Value</i>
Shelf Life	5 y
Theoretical Coverage for 85 mL tube <sup>a)</sup>	<33 500 cm <sup>2</sup> <36 ft <sup>2</sup>

a) Idealized estimate based on 25 µm [1.0 mil] thickness and 100% transfer efficiency.

## Temperature Ranges

<i>Properties</i>	<i>Value</i>
Constant Service Temperature	-68 to 165 °C [-90 to 329 °F]
Storage Temperature Limits	-10 to 40 °C [14 to 104 °F]

## Properties

<i>Thermal Properties</i>	<i>Method</i>	<i>Value</i>
Thermal Conductivity @25 °C [77 °F]	ASTM E 1461	1.0 W/(m·K)
Heat Capacity @25 °C [77 °F]		1.11 J/(g·°C)
Contact Thermal Resistance <sup>a)</sup>	ASTM E 1225	0.71 x 10 <sup>-3</sup> (m <sup>2</sup> ·K)/W

a) Tested with stainless steel plates

<b>Electrical Properties</b>	<b>Method</b>	<b>Value</b>
Volume Resistivity ( $\rho_v$ ) @500 V	ASTM D 257	$9.9 \times 10^9 \Omega \cdot \text{cm}$
Dielectric Strength <sup>a)</sup>	ASTM D 149	4.47 kV
Breakdown Voltage	"	447 V/mil
Dielectric Constant @1 000 cps	ASTM D 150	6.071
@10 000 cps	"	5.847
Dissipation Factor @1 000 cps	"	0.08296
@10 000 cps	"	0.02134
<b>Physical Properties</b>	<b>Method</b>	<b>Value</b>
Color	Visual	White
Filler		Aluminum oxide and boron nitride
Odor		Odorless
Density @25 °C [77 °F]	ASTM D 1475	1.96 g/mL
Viscosity		Thixotropic paste
Dropping Point	ASTM D 2265	>308 °C [>586 °F]
Worked Penetration, 1/2 scale	ASTM D 1403	343
Oil Separation @165 °C [329 °F], 30 h	ASTM D 6184	0.96%
Evaporation Loss @165 °C [329 °F], 22 h	ASTM D 2595	2.34%
Pressure Vessel Oxidation Test @100 h	ASTM D 942	5.5 psi drop
Copper Corrosion @100 °C [212 °F], 24 h	ASTM D 4048	1a, Shiny
Rust Preventive Properties @52 °C [126 °F], 48 h	ASTM D 1743	
Bearing A	"	20% corrosion, fail
Bearing B	"	5% corrosion, fail
Bearing C	"	No corrosion, pass
Water Washout @37 °C [100 °F]	ASTM D 1264	1.45%
Bearing Dried @77 °C [171 °F]		
VOC (Volatile Organic Compound) <sup>b)</sup>	Estimated	69% [31 g/L]
Lubricant		No
Corrosion Resistant		Yes
Bleed resistant		Yes

a) Test as per SAE AS8660: 1/2 inch hemispherical electrodes  
500 V/s rate of rise, 50% R.H. @10 mil gap

b) According to WHIMS regulation

<b>Synthetic Oil Properties</b>	<b>Method</b>	<b>Value</b>
Oil viscosity index <sup>a)</sup>	ASTM D 2270	>110
Fire Point <sup>b)</sup>	ASTM D 92	321 °C [609.8 °F]
Flash Point	ASTM D 92	>290 °C [>554 °F]

Note: Values based on synthetic oil component only.

a) High oil viscosity index of more than a 100 indicate small oil viscosity change with temperature.

b) Temperature at which oil will continue to burn for at least 5 s after ignition with an open flame.

## Storage

Store between -10 °C and 40 °C [14 and 104 °F] in dry area.

## Health, Safety, and Environmental Awareness

Please see the 8617 **Safety Data Sheet** (SDS) for greater details on transportation, storage, handling and other security guidelines.


**Environmental Impact:** The VOC (volatile organic compound) content is 69% [31 g/L] by WHMIS and European standards. Not regulated as a dangerous good for transport.

**Health and Safety:** Wear safety glasses and disposable gloves to avoid exposures.

### HMIS® RATING

<b>HEALTH:</b>	<b>1</b>
<b>FLAMMABILITY:</b>	<b>1</b>
<b>PHYSICAL HAZARD:</b>	<b>0</b>
<b>PERSONAL PROTECTION:</b>	

### NFPA® 704 CODES



*Approximate HMIS and NFPA Risk Ratings Legend:*

0 (Low or none); 1 (Slight); 2 (Moderate); 3 (Serious); 4 (Severe)

## Application Instructions

The conductive grease performance depends on mainly on surface preparation. Improperly prepared contact surfaces can degrade the paste's stability, conductivity, and lubrication characteristics. While the thickness and coverage are also important, the application method itself can easily be adjusted according to performance and application needs.

### Prerequisites

- Wear gloves and protective clothing.
- Clean and dry the surface of the substrate to remove other oils and greases, as well as dust, water, solvents, or any other contaminants.
- *Recommendations:* Use MG 824 Isopropyl Alcohol or MG 4351 Thinner

### Equipment

- Lint free cloth (for cleaning contact and for wiping excess residue)
- Spatula or stick application tools (sized appropriately for your application)
- Isopropyl alcohol or other residue-free organic solvents

### To apply the grease

1. Wipe the contact with a lint-free cloth.
2. Clean the contacts with isopropyl alcohol or other non-oil based cleaner.
3. Once dry, spread grease in a thin layer onto the surface.

## Packaging and Supporting Products

<i>Cat. No.</i>	<i>Packaging</i>	<i>Net Volume</i>		<i>Net Weight</i>		<i>Packaging Weights</i>	
<b>8617-85ML</b>	Tube	85 mL	2.8 fl oz	166 g	5.87 oz	0.2 kg	0.4 lb
<b>8617-1P</b>	Jar	474 mL	1 pint	932 g	2.04 lb	1.0	2.2 lb
<b>8617-1G</b>	Pail	3.78 L	1 gal	7.4 kg	16.3 lb	TBD	TBD

Contact MG Chemicals if custom packaging or sizes are required

TBD=To be determined

### Supporting Products

- *Thinner*: Cat. No. 4351-1L
- *Isopropyl Alcohol*: Cat. No. 824-1L

## Technical Support

Contact us regarding any questions, improvement suggestions, or problems with this product. Application notes, instructions, and FAQs are located at [www.mgchemicals.com](http://www.mgchemicals.com).

Email: [support@mgchemicals.com](mailto:support@mgchemicals.com)

Phone: +(1) 800-340-0772 (Canada, Mexico & USA)

+ (1) 905-331-1396 (International)

Fax: +(1) 905-331-2862 or +(1) 800-340-0773

Mailing address:

#### Manufacturing & Support

1210 Corporate Drive  
Burlington, Ontario, Canada  
L7L 5R6

#### Head Office

9347-193rd Street  
Surrey, British Columbia, Canada  
V4N 4E7

## Warranty

*M.G. Chemicals Ltd.* warrants this product for 12 months from the date of purchase by the end user. *M.G. Chemicals Ltd.* makes no claims as to shelf life of this product for the warranty. The liability of *M.G. Chemicals Ltd.* whether based on its warranty, contracts, or otherwise shall in no case include incidental or consequential damage.

## Disclaimer

This information is believed to be accurate. It is intended for professional end users having the skills to evaluate and use the data properly. *M.G. Chemicals Ltd.* does not guarantee the accuracy of the data and assumes no liability in connection with damages incurred while using it.