

# RUST BLOCK

## 954

RUST PASSIVATOR  
PROTECTION ANTICORROSION

### BENEFITS

- It combines with rust to form a black compound, stable, hard and adherent to the iron.
- It allows the subsequent repainting of corroded surfaces.
- It works at room temperature.
- Allows treated parts to be exposed to the elements.
- Recognized by car manufacturers
- More effective and more concentrated than commercial products usual.



### DEFINITION

Very powerful rust converter, passivator.



2108700 (Bidon 5 kg)

### INSTRUCTIONS FOR USE

Before applying BLOC'ROUILLE on rusty surfaces and to obtain the best results, it is necessary to:

1. Brush to remove loose rust particles, 2. Degrease the surface if necessary with a solvent that is harmless to paints (ORASOLV B30 for example),
3. Apply BLOC'ROUILLE after the solvent has completely dried.  
The treated surface gradually darkens; if the result is not uniform, apply a second coat after 1 hour.  
Apply it at a maximum temperature between 50 and 60 After drying, the product resists to 200 °C.
4. Allow to dry for 16 to 24 hours before applying paint.  
The application is done by brush or spray. The material in this case must be stainless steel, plastic or aluminum.

### FEATURES

Aspect :	Liquide thixotrope
Color :	Crème
Density at 20°C (ASTM D4052):	~ 1.03
Viscosity at 25°C:	100 – 140 cP
pH of pure product:	2.1 to 3
Covering power:	10/15 m <sup>2</sup> /l
Dry extract:	22 to 24%
Liquide ininflammable	

ORAPI® cannot be aware of all the applications in which its products are used and the conditions of their use. ORAPI® assumes no responsibility for: the suitability of its products for a given use or for a particular purpose, the application methods over which it has no control. The information contained in this technical data sheet must in no case replace the preliminary tests that must be carried out to verify the suitability of the product for each intended application. The user of the product described in this technical data sheet remains solely responsible for all measures required to protect people and property against all risks that may result from the implementation and/or use of this product. Consequently, ORAPI® disclaims all implied or explicit warranties, including warranties relating to the fitness for sale or suitability for a particular need, resulting from the sale or use of its products. ORAPI® specifically denies any prosecution for incidental or consequential damages of any kind, including financial operating losses.



# RUST BLOCK

## 954

### RUST PASSIVATOR PROTECTION ANTICORROSION

#### FILM FEATURES

Aspect :	Matte black
Dust-free drying time:	15 mn
- Sec :	30 mn
- Duration: 12 h	

Salt spray resistance: >150 h on rusty plate according to ASTM B 117

COMPLIES with PMUC specifications: Halogen content < 200 ppm

#### FIELD OF APPLICATION

Transport, marine...

Mechanics, mechanical welding...

All sectors using metal parts in oxidizing, saline environments, etc. or requiring protection from rust.

#### PACKAGING

200 kg barrel	ref. 2954U2	x1
Bidon 5 kg	ref. 2954J1	x4
Burette 500 ml	ref. 2954R3	x12



ORAPI® cannot be aware of all the applications in which its products are used and the conditions of their use. ORAPI® assumes no responsibility for: the suitability of its products for a given use or for a particular purpose, the application methods over which it has no control. The information contained in this technical data sheet must in no case replace the preliminary tests that must be carried out to verify the suitability of the product for each intended application. The user of the product described in this technical data sheet remains solely responsible for all measures required to protect people and property against all risks that may result from the implementation and/or use of this product. Consequently, ORAPI® disclaims all implied or explicit warranties, including warranties relating to the fitness for sale or suitability for a particular need, resulting from the sale or use of its products. ORAPI® specifically denies any prosecution for incidental or consequential damages of any kind, including financial operating losses.