

SCHEMA TECNICA



FEROX PRIMER

Primer for Aluminum



DESCRIPTION

Ferox primer - Primer for aluminum is a product based on acrylic resin. The application of the primer guarantees the perfect adhesion of the glazes used for the surface finish, whether nitro or acrylic. Its weather resistance, along with its quick drying, make it ideal for both indoor and outdoor applications.

EMPLOYMENT

Ideal for pre-treating aluminium surfaces.

CLASSIFICATION

USE

Surface preparation: Finely sand the surface with a P600 paper if necessary. Then thoroughly clean the surface from dust and grease. **Application:** shake the can vigorously for at least two minutes. Spray from a distance of 25 cm. Apply two or three light, crossed coats. After use turn the cylinder upside down and spray to the gas only outlet to achieve dispenser cleanliness. Can be overpainted after 2-4 hours. Any product stains can be removed with acetone and/or nitro thinner.

WARNINGS

Arexons guarantees compatibility between the paints of its own production, before carrying out the work make sure of compatibility with paints/primers from other manufacturers. For information on product safety, please consult the Safety Data Sheet. In case of storage or use in conditions other than those indicated, please contact the company

STORAGE

At least 3 years if stored under the following conditions: in the original packaging and sealed, away from direct sunlight, in a temperature range of 5°C to 35°C.

PACKAGING

Cod. 2013 aerosol can 400 ml

I dati contenuti in questo stampato sono frutto di ricerche tecnologiche dei nostri laboratori e vengono dati a puro titolo informativo. Escludiamo ogni responsabilità che derivi da scelta o applicazione errata del prodotto e dalla mancanza delle necessarie precauzioni, che dovranno essere verificate attentamente dall'utilizzatore.

Si declina ogni responsabilità per qualsiasi informazione tecnica o servizio di consulenza fornito a titolo gratuito dal nostro servizio clienti.

Per informazioni, rivolgersi al nostro Servizio Tecnico al n° 800-016604

AREXONS S.p.A. A SOCIO UNICO

Via Antica di Cassano, 23

20063 Cernusco sul Naviglio (MI) Italy

Capitale Sociale: € 15.000.000 I.V.

Registro delle Imprese di Milano n. 09728360968

Codice Fiscale e Partita IVA 09728360968

Direzione e coordinamento ex art. 2497 c.c. PLI (Netherlands) B.V.

Centralino 02 92436.1

Fax 02 92436.306

www.arexons.com



A wholly-owned subsidiary of PETRONAS



EXPERIENCE TO PERFORM

SCHEMA TECNICA

FEATURES

• Base	Synthetic resin
• Aspect	Aerosol
• Color	Dark grey
• Yield per can	0.8 m2
• Wither	
	Dust-free 15 minutes
	dry to the touch 30 minutes
	Dry in depth 2-4 hours
• Propellant	Propane-Butane

The above data do not constitute specifications and are subject to normal manufacturing tolerances

NOTES

For information on product safety, we recommend that you consult the safety data sheet.

T.S. 17.12.2024

I dati contenuti in questo stampato sono frutto di ricerche tecnologiche dei nostri laboratori e vengono dati a puro titolo informativo. Escludiamo ogni responsabilità che derivi da scelta o applicazione errata del prodotto e dalla mancanza delle necessarie precauzioni, che dovranno essere verificate attentamente dall'utilizzatore.

Si declina ogni responsabilità per qualsiasi informazione tecnica o servizio di consulenza fornito a titolo gratuito dal nostro servizio clienti.

Per informazioni, rivolgersi al nostro Servizio Tecnico al n° 800-016604

AREXONS S.p.A. A SOCIO UNICO

Via Antica di Cassano, 23

20063 Cernusco sul Naviglio (MI) Italy

Capitale Sociale: € 15.000.000 I.V.

Registro delle Imprese di Milano n. 09728360968

Codice Fiscale e Partita IVA 09728360968

Direzione e coordinamento ex art. 2497 c.c. PLI (Netherlands) B.V.

Centralino 02 92436.1

Fax 02 92436.306

www.arexons.com



A wholly-owned subsidiary of PETRONAS