

## MATERIAL SAFETY DATA SHEET

### INTRODUCTION.

This Material Safety Data Sheet contains information relevant to all types of vitrified abrasive products. Reference must be made to the relevant product code when carrying out assessments.

### SECTION 1 PRODUCT IDENTIFICATION AND MANUFACTURE

#### MANUFACTURER'S / SUPPLIERS NAME.

##### NAME AND ADDRESS

Saint-Gobain Abrasives Limited  
Doxey Road  
Stafford ST16 1EA

TEL NO. (01785) 222000  
FACSIMILE (01785) 213487

##### CHEMICAL NAME AND SYNONYMS

Vitrified Abrasive Products.  
Norton, Flexovit and Baystate (Brands)  
Signified by the letter 'V' in the product mark.  
A typical mark is WA 603 K6V LGAA

##### TRADE NAMES AND SYNONYMS

Vitrified Grinding Wheels, Cups, Dishes, Rings, Cones, Rollers, Segments, Blocks, Hones, Mounted Points & Mounted Wheels.

### SECTION 2 COMPOSITION / INFORMATION ON INGREDIENTS

##### CHEMICAL NAME

Silicon Carbide (Pre-REACH No. 05-2114087228-42-0000)  
Aluminium Oxide  
Fused Silicates.

CONSTITUENT	CAS. No.	RANGE BY % MASS	EH40 DESIGNATION		EH40 STANDARD
			mg m <sup>-3</sup> 8hr TWA Total Inhalable	Respirable	
Glass Oxide	-	1-50	10	4	OES
Silicon Carbide	409-21-2	30 -50	10	4	OES
Aluminium Oxide	1344-28-1	10-95	10	4	OES
*Silica Crystalline	-	0-0.2	-	0.3	MEL

#### IMPREGNATES

Some vitrified products may contain one of the following materials as an impregnate within the structure.

Wax	8002-74-2	1-20	2(as fume)	-	OES
Sulphur	7704-34-9	1-40	10	4	OES
Rosin	8050-09-7	1-20	10	4	OES

### BUSHING MATERIAL

As well as plain bore grinding wheels, bushed products are available and may contain one or more of the following materials.

CONSTITUENT	Cas No.	RANGE BY % MASS	EH40 DESIGNATION mg m <sup>-3</sup> 8hr TWA Total Inhalable Respirable	Respirable	EH40 STANDARD
Polystyrene Plastic	713-020-005	0-5	-	-	-
Mastic bore lining consisting of: Calcium Carbonate	1317-65-3		10	4	OES
Talc (Magnesium Silicate)	14807-96-6		10	4	OES
Adhesive	67-64-1		10	4	OES
Lithopone	1309-37-1		10	4	OES
Graphite	7440-44-0		10	5	OES
Glass Fibres	14808-60-7 1344-28-1 13463-67-7 1309-48-4 1303-86-2 1313-50-3 1305-78-8 12136-47-7	53 – 60 11 – 15.5 0 – 3 10 – 12.5 0 – 9 <1 10 – 12.5 <1	10	4	OES

These materials are not in the grinding zone and consequently do not present a hazard in normal use.

### SECTION 3 SUBSTANCE HAZARD IDENTIFICATION

Vitrified grinding wheels are not considered a hazardous product under CHIP regulations. In normal use users are advised to maintain particulate exposure below the Occupational Exposure Limit for nuisance dusts as defined in the latest EH40 publication.

The hazards associated with the use of impregnated wheels are:-

Sulphur impregnation; heat build up during dry grinding may produce low level sulphur dioxide fumes.

Wax impregnation; heat build up may produce low level wax fumes.

#### SECTION 4 FIRST AID MEASURES

Due to the extensive use of coolant during most grinding applications the level of risk of exposure to inhalation is minimised. Nuisance dust will be generated when dry grinding therefore LEV control should be applied if levels need controlling below the OES for nuisance dusts.

<b>INHALATION</b>	<p>If a major exposure occurs, exposed personnel should be removed to fresh air until the level of air borne particulate subsides. Medical attention should be sought if breathing difficulties are experienced.</p> <p>The crystalline silica content is very low and is expected to be locked in the glass bond excessive exposure is unlikely.</p>
<b>SKIN CONTACT</b>	<p>Wash exposed skin with water. Mechanical abrasion may occur on exposed skin increasing the potential of bacteria or other substance attack. If irritation occurs seek medical attention.</p>
<b>EYE CONTACT</b>	<p>Due to the abrasive nature of particulate, irritation may occur. Eyes should be flushed copiously and medical attention sought if symptoms persist.</p>

#### SECTION 5 FIRE FIGHTING MEASURES

Abrasive grain is none combustible. Impregnated wheels may evolve normal combustion products and or Sulphur dioxide.

#### SECTION 6 ACCIDENTAL RELEASE MEASURES

<b>PERSONAL PROTECTION</b>	<p>If conditions are dusty a dust mask should be worn.</p> <p>If there is a potential for eye contact eye protection is recommended.</p>
<b>ENVIRONMENTAL PRECAUTIONS</b>	<p>Waste particulate must be bagged and sealed then disposed of as general waste.</p>
<b>METHODS FOR CLEARING UP</b>	<p>Spillage's should be cleaned up by wet sweeping or vacuum.</p>

#### SECTION 7 HANDLING AND STORAGE

<b>HANDLING PRECAUTIONS</b>	<p>Use of the grinding wheels must be in compliance with the 'Safety in the Use of Abrasive Wheels' HS(G) 17 available from HSE books.</p> <p>Also refer to F.E.P.A Safety Code for the Use, Care and Protection of Abrasive Wheels.</p> <p>The user should ensure correct product selection according to operating conditions.</p>
<b>STORAGE INCLUDING ANY SPECIAL REQUIREMENTS</b>	<p>Vitrified wheels should be protected from acid oil and frost and excessive temperature variation in storage.</p> <p>Machine coolant will cause the wheel to be out of balance if allowed to gather in one half of the wheel. Coolant should be drained off before storage.</p> <p>Reference to the above documents will identify the relevant storage requirements for a given product type and providing the product is stored under carefully controlled conditions in accordance with the information in this section and the above guidance the shelf life is indefinite.</p>

<b>SECTION 8 EXPOSURE CONTROL/PERSONAL PROTECTION</b>	
<b>ENGINEERING CONTROLS /VENTILATION</b>	LEV must be provided if the OES standard as stated in the latest edition of EH40 for nuisance particulate is exceeded.
<b>RESPIRATORY PROTECTION</b>	Dust masks may be worn for low level short term exposure.
<b>EYE PROTECTION</b>	Impact resistant eye protection must be worn when using grinding wheels.
<b>HAND/SKIN PROTECTION</b>	If regular exposure to abrasive particulate occurs gloves and overalls are recommended.

<b>SECTION 9 PHYSICAL AND CHEMICAL PROPERTIES</b>	
<b>BOILING POINT °C</b>	-
<b>FLASH POINT °C</b>	-
<b>SOLUBILITY IN WATER</b>	Not miscible
<b>VAPOUR PRESSURE</b>	N/A
<b>IGNITION TEMPERATURE °C</b>	-

<b>SECTION 10 STABILITY AND REACTIVITY PROPERTIES</b>	
<b>STABILITY</b>	Very stable
<b>CONDITIONS TO AVOID</b>	Excessive heat during use may lead to thermal shock causing the wheel to burst. No alterations must be carried out on the product. Consult your Saint-Gobain Abrasives technical representative for advice.
<b>COMBUSTION PRODUCTS</b>	Wheels containing impregnates may evolve toxic gases in a fire

<b>SECTION 11 TOXICOLOGICAL INFORMATION</b>	
<b>ACUTE TOXICITY:-</b>	None known

<b>SECTION 12 ECOLOGICAL INFORMATION</b>	
<b>DEGRADABILITY</b>	Will not degrade
<b>ACUTE FISH TOXICITY</b>	None known
<b>WATER HAZARD CLASSIFICATION</b>	N/A

### SECTION 13 DISPOSAL CONSIDERATIONS

<b>DISPOSAL METHODS</b>	General waste
-------------------------	---------------

### SECTION 14 TRANSPORT INFORMATION

Special transportation precautions do not apply. However care should be taken to avoid mechanical damage during transportation.

### SECTION 15 REGULATORY INFORMATION

#### PRODUCT LABEL DETAILS - PER CHIP

<b>PRODUCT TRADE NAME</b>	Vitrified (bonded) abrasive products
<b>HAZARD SYMBOL</b>	Not classified as hazardous
<b>RISK PHRASE No's &amp; WORDS</b>	N/A
<b>SAFETY PHRASE No's &amp; WORDS</b>	N/A

Specific regulations governing the use of abrasive products has been extensively revoked. For guidance as to the general requirements reference should be made to the requirements under the European (6 pack) regulations and any revisions.

### SECTION 16 OTHER INFORMATION

<b>TRAINING ADVISE</b>	In accordance with the requirements of the provision and use of work equipment regulations 1992, users of grinding wheels must be trained in the appropriate wheel mounting course, be certified and their name entered on a company register.
<b>RECOMMENDED USES &amp; RESTRICTIONS</b>	Use of the grinding wheels must be in compliance with the 'Safety in the Use of Abrasive Wheels HS(G) 17 available from HSE books.  Also refer to F.E.P.A Safety Code for the Use, Care and Protection of Abrasive Wheels.  The user should ensure correct product selection according to operating conditions.

Although Saint-Gobain Abrasives Ltd. has attempted to provide accurate and current information herein, Saint-Gobain Abrasives Ltd. makes no representations regarding the accuracy or completeness of the information and assumes no liability for any loss, damage or injury of any kind, which may result from or arise out of the use or reliance on this information by any person.