

## No-Clean Super Wick™

### Description

No-Clean Super Wick™ is a tightly woven, oxide-free copper braid coated with a high activation temperature no-clean flux. Its high purity and tight weave make it fast-wicking, quickly removing solder and minimizing dwell time.

It is suitable for general purpose solder removal, including reworking and repairing of circuit boards, benchtop repair and service, through-hole repair, and surface mount assembly touch-up.

### Features and Benefits

- Flux residue is non-conductive and non-corrosive
- Available in 1.5, 2.0 and 2.5 mm widths
- Available in 1.5 and 15 m lengths
- ESD safe bobbins for 1.5 m size
- NSF—nonfood compounds program listed

### Desoldering Braid Selection Guide

| Cat No. | Width |     | Length |     | ESD Safe Spools | Label Color Code |
|---------|-------|-----|--------|-----|-----------------|------------------|
|         | in    | mm  | ft     | m   |                 |                  |
| 424-NS  | 0.06  | 1.5 | 5      | 1.5 | Yes             | YELLOW           |
| 425-NS  | 0.08  | 2.0 | 5      | 1.5 | Yes             | GREEN            |
| 453-NS  | 0.08  | 2.0 | 50     | 15  | No              | GREEN            |
| 426-NS  | 0.10  | 2.5 | 5      | 1.5 | Yes             | BLUE             |
| 454-NS  | 0.10  | 2.5 | 50     | 15  | No              | BLUE             |

## Flux Properties

High temperature, mildly activated rosin flux. Further, this flux is non-corrosive.

| Physical Properties   | Method                                | Value                 |
|-----------------------|---------------------------------------|-----------------------|
| Flux classification   | Conforms to MIL-F-14256F<br>J-STD-004 | R (Rosin)<br>ROLO     |
| Flux percentage       | —                                     | <5%                   |
| Corrosion             | JIS Z 3197 and QQ-SS-571d             | Non-corrosive residue |
| Cleaning requirements | —                                     | Recommended           |

## Compatibility

**Chemical**—The flux residue from the Super Wick™ is inert under normal conditions. The flux residue can be cleaned with a flux cleaner like the MG 4140 or 413B.

## Storage

Store between 22 to 27 °C [72 to 81 °F] in a dry area, away from sunlight. Keep away from moisture. Shrink wrapping is recommended for extended storage.

## Health and Safety

Please see the 400-NS Series Safety Data Sheet (SDS) for further details on transportation, storage, handling, safety guidelines, and regulatory compliance.

## Application Instructions

Wicking works best for the removal of surface solders. This desoldering method is not recommended for removal of solder in through plated holes. Choose a braid that matches the size of the solder to be removed. If there are small beads, choosing a wider braid will also speed up the desoldering process.

### Removing surface solder:

1. Remove conformal coating or any contamination that may be present.
2. Heat up the soldering iron. For lead-free solder, start with tip temperature of about 315 °C (599 °F) and adjust as necessary.
3. (Optional) Apply flux to the lead or land area.
4. Set the braid on the solder to be removed and
5. Place the solder tip on the braid, avoiding contact with other components.
6. When wicking action has ended, remove the soldering iron and braid together in perpendicular motion from the surface.
7. Cut off the used section of the braid and discard.
8. Let the area cool, clean the tip with the sponge, and repeat removal steps as necessary.
9. Clean flux residue that may have accumulated.

## Technical Support

Please contact us regarding any questions, suggestions for improvements, or problems with this product. Application notes, instructions and FAQs are located at [www.mgchemicals.com](http://www.mgchemicals.com).

**Email:** [support@mgchemicals.com](mailto:support@mgchemicals.com)

**Phone:** +(1) 800-340-0772 (Canada, Mexico & USA)

+ (1) 905-331-1396 (International)

+ (44) 1663 362888 (UK & Europe)

**Fax:** +(1) 905-331-2862 or +(1) 800-340-0773

**Mailing address: Manufacturing & Support**  
1210 Corporate Drive  
Burlington, Ontario, Canada  
L7L 5R6

**Head Office**  
9347-193rd Street  
Surrey, British Columbia, Canada  
V4N 4E7

## Disclaimer

This information is believed to be accurate. It is intended for professional end users who have the skills required to evaluate and use the data properly. M.G. Chemicals Ltd. does not guarantee the accuracy of the data and assumes no liability in connection with damages incurred while using it.