

Notice for TAIYO YUDEN products

Please read this notice before using the TAIYO YUDEN products.



REMINDERS

- Product information in this catalog is as of October 2008. All of the contents specified herein are subject to change without notice due to technical improvements, etc. Therefore, please check for the latest information carefully before practical application or usage of the Products.

Please note that Taiyo Yuden Co., Ltd. shall not be responsible for any defects in products or equipment incorporating such products, which are caused under the conditions other than those specified in this catalog or individual specification.

- Please contact Taiyo Yuden Co., Ltd. for further details of product specifications as the individual specification is available.

- Please conduct validation and verification of products in actual condition of mounting and operating environment before commercial shipment of the equipment.

- All electronic components or functional modules listed in this catalog are developed, designed and intended for use in general electronics equipment.(for AV, office automation, household, office supply, information service, telecommunications, (such as mobile phone or PC) etc.). Before incorporating the components or devices into any equipment in the field such as transportation,(automotive control, train control, ship control), transportation signal, disaster prevention, medical, public information network (telephone exchange, base station) etc. which may have direct influence to harm or injure a human body, please contact Taiyo Yuden Co., Ltd. for more detail in advance.

Do not incorporate the products into any equipment in fields such as aerospace, aviation, nuclear control, submarine system, military, etc. where higher safety and reliability are especially required.

In addition, even electronic components or functional modules that are used for the general electronic equipment, if the equipment or the electric circuit require high safety or reliability function or performances, a sufficient reliability evaluation check for safety shall be performed before commercial shipment and moreover, due consideration to install a protective circuit is strongly recommended at customer's design stage.

- The contents of this catalog are applicable to the products which are purchased from our sales offices or distributors (so called "TAIYO YUDEN' s official sales channel").

It is only applicable to the products purchased from any of TAIYO YUDEN' s official sales channel.

- Please note that Taiyo Yuden Co., Ltd. shall have no responsibility for any controversies or disputes that may occur in connection with a third party's intellectual property rights and other related rights arising from your usage of products in this catalog. Taiyo Yuden Co., Ltd. grants no license for such rights.

- Caution for export

Certain items in this catalog may require specific procedures for export according to "Foreign Exchange and Foreign Trade Control Law" of Japan, "U.S. Export Administration Regulations," and other applicable regulations. Should you have any question or inquiry on this matter, please contact our sales staff.

Should you have any question or inquiry on this matter, please contact our sales staff.

一般積層セラミックコンデンサ

(高誘電率系・Class 2)

STANDARD MULTILAYER CERAMIC CAPACITORS (CLASS2 :HIGH DIELECTRIC CONSTANT TYPE)

	Code	Temp.characteristics	Operating temp. range
OPERATING TEMP.	BJ	B	-25~+85°C
		X5R*	-55~+85°C
	B7	X7R	-55~+125°C
		F	-25~+85°C
	F	Y5V	-30~+85°C

*個別仕様の取交しにより、X7R/X7S 仕様に対応している場合があります。

*We may provide X7R/X7S for some items according to the individual specification.



特長 FEATURES

- ・実装密度の向上が図れます
- ・モノリシックの構造のため、信頼性が高い
- ・同一形状、静電容量範囲が広い

- ・ Improve Higher Mounting Densities.
- ・ Multilayer block structure provides higher reliability
- ・ A wide range of capacitance values available in standard case sizes.

用途 APPLICATIONS

- ・ 一般電子機器用
- ・ 通信機器用 (携帯電話、PHS、コードレス電話 etc.)


- ・ General electronic equipment
- ・ Communication equipment (cellular phone, PHS, other wireless applications, etc.)

形名表記法 ORDERING CODE

1 定格電圧 [VDC] A 4 J 6.3 L 10 E 16 T 25 G 35 U 50	4 形状寸法 (EIA) L×W [mm] 042(01005) 0.4×0.2 063(0201) 0.6×0.3 105(0402) 1.0×0.5	6 公称静電容量 [pF] 例 102 1000 223 22000	7 容量許容差 K ±10% M ±20% Z +80% -20%	9 個別仕様 - 標準
2 シリーズ名 M 積層コンデンサ	5 温度特性 BJ B X5R B7 X7R F Y5V △=スペース		8 製品厚み [mm] C 0.2 P 0.3 V 0.5	10 包装 F φ178mm テーピング (2mmピッチ)
3 端子電極 K メッキ品				11 当社管理記号 △ 標準 △=スペース

L	M	K	1	0	5	B	J	1	0	4	K	V	-	F	△
1	2	3	4	5	6	7	8	9	10	11					

1 Rated voltage [VDC] A 4 J 6.3 L 10 E 16 T 25 G 35 U 50	4 Dimensions (case size) (L×W) (mm) 042(01005) 0.4×0.2 063(0201) 0.6×0.3 105(0402) 1.0×0.5	6 Nominal capacitance [pF] example 102 1000 223 22000	7 Capacitance tolerance K ±10% M ±20% Z +80% -20%	9 Special code - Standard products
2 Series name M Multilayer ceramic capacitor	5 Temperature characteristics code BJ B X5R B7 X7R F Y5V △=Blank space		8 Thickness [mm] C 0.2 P 0.3 V 0.5	10 Packaging F φ178mm Taping (2mm pitch)
3 End termination K Plated				11 Internal code △ Standard Products △=Blank space



Type (EIA)	L	W	T	e
□MK042 (01005)	0.4±0.02 (0.016±0.001)	0.2±0.02 (0.008±0.001)	0.2±0.02 (0.008±0.001)	C 0.1±0.03 (0.004±0.001)
□MK063 (0201)	0.6±0.03 (0.024±0.001)	0.3±0.03 (0.012±0.001)	0.3±0.03 (0.012±0.001)	P 0.15±0.05 (0.006±0.002)
□MK105 (0402)	1.0±0.05*1 (0.039±0.002)	0.5±0.05*1 (0.020±0.002)	0.5±0.05*1 (0.020±0.002)	V 0.25±0.10 (0.010±0.004)

注: *1 ±0.1mm 公差あり

Note: *1. Including dimension tolerance±0.1mm

Unit : mm (inch)

概略バリエーション AVAILABLE CAPACITANCE RANGE

■汎用積層セラミックコンデンサ (General Multilayer Ceramic capacitors)

Cap [pF]	Type	042		063								105																	
	Temp.char.	B/X5R		B/X5R				X5R				B/X7R			B/X5R						X5R			F/Y5V					
	VDC	10V	6.3V	25V	16V	10V	10V	6.3V	4V	50V	25V	16V	50V	35V	25V	16V	10V	6.3V	10V	6.3V	4V	50V	25V	16V	10V	6.3V			
	[pF:3digits]																												
100	101																												
150	151																												
220	221																												
330	331																												
470	471																												
680	681																												
1000	102																												
1500	152																												
2200	222																												
3300	332																												
4700	472																												
6800	682																												
10000	103																												
15000	153																												
22000	223																												
33000	333																												
47000	473																												
68000	683																												
100000	104																												
220000	224																												
330000	334																												
470000	474																												
1000000	105																												
2200000	225																												
3300000	335																												
4700000	475																												

注: グラフの記号は製品厚み記号です。Note : Letters in the table indicate thickness.

温度特性コード Temp.char.Code	温度特性 Temperature characteristics					静電容量許容差[%] Capacitance tolerance	tan δ [%] Dissipation factor
	準拠規格 Applicable standard		温度範囲[℃] Temperature range	基準温度[℃] Ref. Temp.	静電容量変化率[%] Capacitance change		
	JIS	B	-25~+85	20	±10		
B/BJ	EIA	X5R	-55~+85	25	±15	±10 (K) ±20 (M)	2.5 max.*
B7	EIA	X7R	-55~+125	25	±15		
F	JIS	F	-25~+85	20	+30/-80	+80 (Z) -20	7.0 max.*
	EIA	Y5V	-30~+85	25	+22/-82		

*: 代表的な値を記載しています。詳細はアイテム一覧を参照ください。

*: The figure indicate typical value. Please refer to PART NUMBERS table.

セレクションガイド
Selection Guide






アイテム一覧
Part Numbers

特性図
Electrical Characteristics

梱包
Packaging

信頼性
Reliability Data

使用上の注意
Precautions



etc

■ 042TYPE (01005 case size)

【温度特性 Temp.char. BJ:B/X5R】

定格電圧 Rated Voltage	形 名 Ordering code		EHS (Environmental Hazardous Substances)	公 称 静電容量 Capacitance [pF]	温度特性 Temperature characteristics	tan δ Dissipation factor [%] Max.	実装条件 Soldering method R:リフロー Reflow soldering W: フロー Wave soldering	静電容量 許 容 差 Capacitance tolerance	厚 み Thickness [mm] (inch)				
10V	LMK042 BJ101 □ C		RoHS	100	B/X5R*2	5	R	± 10% ± 20%	0.2 ± 0.02 (0.008 ± 0.001)				
	LMK042 BJ151 □ C		RoHS	150									
	LMK042 BJ221 □ C		RoHS	220									
	LMK042 BJ331 □ C		RoHS	330									
	LMK042 BJ471 □ C		RoHS	470									
	LMK042 BJ681 □ C		RoHS	680									
	LMK042 BJ102 □ C		RoHS	1000									
6.3V	JMK042 BJ152 □ C*1		RoHS	1500						10			
	JMK042 BJ222 □ C*1		RoHS	2200									
	JMK042 BJ332 □ C*1		RoHS	3300									
	JMK042 BJ472 □ C*1		RoHS	4700									
	JMK042 BJ682 □ C*1		RoHS	6800									
	JMK042 BJ103 □ C*1		RoHS	10000									

形名の□には静電容量許容差記号が入ります。

*1 高温負荷試験の試験電圧は定格電圧の 1.5 倍

*2 個別仕様の取扱いにより、X7R/X7S仕様に対応している場合があります。

□ Please specify the capacitance tolerance code.

*1 Test Voltage of Loading at high temperature test is 1.5 time of the rated voltage.

*2 We may provide X7R/X7S for some items according to the individual specification.

■ 063TYPE (0201 case size)

【温度特性 Temp.char. BJ:B/X5R】

定格電圧 Rated Voltage	形 名 Ordering code		EHS (Environmental Hazardous Substances)	公 称 静電容量 Capacitance [pF]	温度特性 Temperature characteristics	tan δ Dissipation factor [%] Max.	実装条件 Soldering method R: リフロー Reflow soldering W: フロー Wave soldering	静電容量 許 容 差 Capacitance tolerance	厚 み Thickness [mm] (inch)					
25V	TMK063 BJ101□P		RoHS	100	B/X5R*2	3.5	R	±10% ±20%	0.3±0.03 (0.012 ± 0.001)					
	TMK063 BJ151□P		RoHS	150										
	TMK063 BJ221□P		RoHS	220										
	TMK063 BJ331□P		RoHS	330										
	TMK063 BJ471□P		RoHS	470										
	TMK063 BJ681□P		RoHS	680										
16V	TMK063 BJ102□P		RoHS	1000	B/X5R*2	5		R		±10% ±20%	0.3±0.03 (0.012 ± 0.001)			
	EMK063 BJ152□P		RoHS	1500										
	EMK063 BJ222□P		RoHS	2200										
10V	EMK063 BJ332□P		RoHS	3300	B/X5R*2	7.5						R	±10% ±20%	0.3±0.03 (0.012 ± 0.001)
	LMK063 BJ472□P		RoHS	4700										
	LMK063 BJ682□P		RoHS	6800										
	LMK063 BJ103□P		RoHS	10000										
	LMK063 BJ223□P*1		RoHS	22000										
6.3V	LMK063 BJ473□P*1		RoHS	47000	X5R	7.5	R		±10% ±20%	0.3±0.03 (0.012 ± 0.001)				
	LMK063 BJ104□P*1		RoHS	100000										
	JMK063 BJ473□P*1		RoHS	47000										
	JMK063 BJ104□P*1		RoHS	100000										
4V	JMK063 BJ224MP*1,*3		RoHS	220000	X5R	10		R			±20%		0.3±0.03 (0.012 ± 0.001)	
	AMK063 BJ224MP*1		RoHS	220000										
	AMK063 BJ334MP*1,*3		RoHS	330000										
4V	AMK063 BJ474MP*1,*3		RoHS	470000	X5R	10			R			±20%		0.3±0.03 (0.012 ± 0.001)
	AMK063 BJ334MP*1,*3		RoHS	330000										

形名の□には静電容量許容差記号が入ります。

*1 高温負荷試験の試験電圧は定格電圧の 1.5 倍

*2 個別仕様の取扱いにより、X7R仕様に対応している場合があります。

*3 ご使用の回路や機器により、個別仕様の取り交わしが必要になります。
必ず正規販売チャンネルにお問い合わせください。

□ Please specify the capacitance tolerance code.

*1 Test Voltage of Loading at high temperature test is 1.5 time of the rated voltage.

*2 We may provide X7R for some items according to the individual specification.

*3 The exchange of individual specification is necessary depending on the application and circuit condition. Please contact Taiyo Yuden sales channel.

■ 105TYPE (0402 case size)

【温度特性 Temp.char. BJ:B/X5R】

定格電圧 Rated Voltage	形 名 Ordering code		EHS (Environmental Hazardous Substances)	公 称 静電容量 Capacitance [pF]	温度特性 Temperature characteristics	tan δ Dissipation factor [%] Max.	実装条件 Soldering method R: リフロー Reflow soldering W: フロー Wave soldering	静電容量 許 容 差 Capacitance tolerance	厚 み Thickness [mm] (inch)		
50V	UMK105 BJ221□V		RoHS	220	B/X5R*2	2.5	R	±10% ±20%	0.5±0.05 (0.02 ± 0.002)		
	UMK105 BJ331□V		RoHS	330							
	UMK105 BJ471□V		RoHS	470							
	UMK105 BJ681□V		RoHS	680							
	UMK105 BJ102□V		RoHS	1000							
	UMK105 BJ152□V		RoHS	1500							
	UMK105 BJ222□V		RoHS	2200							
	UMK105 BJ332□V		RoHS	3300							
	UMK105 BJ472□V		RoHS	4700							
	UMK105 BJ682□V*1		RoHS	6800		3.5					
UMK105 BJ103□V		RoHS	10000								
35V	GMK105 BJ104□V*1		RoHS	100000	B/X5R	5					
25V	TMK105 BJ682□V		RoHS	6800	B/X5R*2	2.5					
	TMK105 BJ103□V		RoHS	10000		3.5					
	TMK105 BJ153□V		RoHS	15000							
	TMK105 BJ223□V		RoHS	22000							
	TMK105 BJ333□V*1		RoHS	33000							
	TMK105 BJ473□V*1		RoHS	47000							
TMK105 BJ104□V*1		RoHS	100000	B/X5R	5						
16V	EMK105 BJ333□V		RoHS	33000	B/X5R*2	3.5					
	EMK105 BJ473□V		RoHS	47000							
	EMK105 BJ683□V		RoHS	68000	B/X5R	5					
	EMK105 BJ104□V*1		RoHS	100000	B/X5R*2						
	EMK105 BJ224□V*1		RoHS	220000							
10V	LMK105 BJ104□V		RoHS	100000	B/X5R						
	LMK105 BJ224□V*1		RoHS	220000							
	LMK105 BJ474□V*1		RoHS	470000	X5R	10					
	LMK105 BJ105□V*1		RoHS	1000000							
6.3V	JMK105 BJ224□V*1		RoHS	220000	B/X5R	5					
	JMK105 BJ474□V*1		RoHS	470000							
	JMK105 BJ105□V*1		RoHS	1000000							
	JMK105 BJ225MV*1,*3		RoHS	2200000				X5R	10	±20%	0.5±0.1 (0.02 ± 0.004)
4V	AMK105 BJ335MV*1,*3		RoHS	3300000							
	AMK105 BJ475MV*1,*3		RoHS	4700000							

形名の□には静電容量許容差記号が入ります。

*1 高温負荷試験の試験電圧は定格電圧の 1.5 倍

*2 個別仕様の取交しにより、X7R仕様に対応している場合があります。

*3 ご使用の回路や機器により、個別仕様の取り交わしが必要になります。
必ず正規販売チャンネルにお問い合わせください。

□ Please specify the capacitance tolerance code.

*1 Test Voltage of Loading at high temperature test is 1.5 time of the rated voltage.

*2 We may provide X7R for some items according to the individual specification.

*3 The exchange of individual specification is necessary depending on the application and circuit condition. Please contact Taiyo Yuden sales channel.

【温度特性 Temp.char. B7:X7R】

定格電圧 Rated Voltage	形 名 Ordering code		EHS (Environmental Hazardous Substances)	公 称 静電容量 Capacitance [pF]	温度特性 Temperature characteristics	tan δ Dissipation factor [%] Max.	実装条件 Soldering method R: リフロー Reflow soldering W: フロー Wave soldering	静電容量 許 容 差 Capacitance tolerance	厚 み Thickness [mm] (inch)
50V	UMK105 B7 221□V		RoHS	220	X7R	2.5	R	±10% ±20%	0.5±0.05 (0.02 ± 0.002)
	UMK105 B7 331□V		RoHS	330					
	UMK105 B7 471□V		RoHS	470					
	UMK105 B7 681□V		RoHS	680					
	UMK105 B7 102□V		RoHS	1000					
	UMK105 B7 152□V		RoHS	1500					
	UMK105 B7 222□V		RoHS	2200					
	UMK105 B7 332□V		RoHS	3300					
	UMK105 B7 472□V* ¹		RoHS	4700					
	UMK105 B7 682□V* ¹		RoHS	6800					
UMK105 B7 103□V* ¹		RoHS	10000		3.5				
25V	TMK105 B7 472□V		RoHS	4700		2.5			
	TMK105 B7 682□V		RoHS	6800		3.5			
	TMK105 B7 103□V		RoHS	10000					
	TMK105 B7 153□V* ¹		RoHS	15000					
	TMK105 B7 223□V* ¹		RoHS	22000					
	TMK105 B7 333□V* ¹		RoHS	33000					
	TMK105 B7 473□V* ¹		RoHS	47000					
16V	EMK105 B7 153□V		RoHS	15000		5			
	EMK105 B7 223□V		RoHS	22000					
	EMK105 B7 333□V		RoHS	33000					
	EMK105 B7 473□V		RoHS	47000					
	EMK105 B7 104□V* ¹		RoHS	100000					

形名の□には静電容量許容差記号が入ります。

*1 高温負荷試験の試験電圧は定格電圧の 1.5 倍

□ Please specify the capacitance tolerance code.

*1 Test Voltage of Loading at high temperature test is 1.5 time of the rated voltage.

【温度特性 Temp.char. F:Y5V】

定格電圧 Rated Voltage	形 名 Ordering code		EHS (Environmental Hazardous Substances)	公 称 静電容量 Capacitance [pF]	温度特性 Temperature characteristics	tan δ Dissipation factor [%] Max.	実装条件 Soldering method R: リフロー Reflow soldering W: フロー Wave soldering	静電容量 許 容 差 Capacitance tolerance	厚 み Thickness [mm] (inch)
50V	UMK105 F103ZV		RoHS	10000	F/Y5V	5	R	+80% -20%	0.5±0.05 (0.02 ± 0.002)
25V	TMK105 F223ZV		RoHS	22000					
16V	EMK105 F473ZV		RoHS	47000		7			
	EMK105 F104ZV		RoHS	100000		9			
10V	LMK105 F224ZV		RoHS	220000		11			
6.3V	JMK105 F474ZV		RoHS	470000		12.5			
	JMK105 F105ZV* ¹		RoHS	1000000		20			

*1 高温負荷試験の試験電圧は定格電圧の 1.5 倍

*1 Test Voltage of Loading at high temperature test is 1.5 time of the rated voltage.

梱包 PACKAGING

①最小受注単位数 Minimum Quantity


■テーピング梱包 Taped packaging

形式 (EIA) Type	製品厚み Thickness		標準数量 Standard quantity [pcs]	
	mm (inch)	code	紙テープ paper	エンボステープ Embossed tape
□MK042 (01005)	0.2 (0.008)	C	15000	—
□MK063 (0201)	0.3 (0.012)	P	15000	—
□2K096 (0302)	0.3 (0.012)	P	10000	—
	0.45 (0.018)	K		
□WK105 (0204)	0.3 (0.012)	P	10000	—
□MK105 (0402)	0.5 (0.020)	V, W	10000	—
□VK105 (0402)		W		
□MK107 (0603) □WK107 (0306)	0.45 (0.018)	K	4000	—
	0.5 (0.020)	V	—	4000
	0.8 (0.031)	A	4000	—
□2K110 (0504)	0.5 (0.020)	V	4000	—
	0.8 (0.031)	A	4000	—
	0.6 (0.024)	B	4000	—
□MK212 (0805) □WK212 (0508)	0.45 (0.018)	K	4000	—
	0.85 (0.033)	D	4000	—
	1.25 (0.049)	G	—	3000
□4K212 (0805) □2K212 (0805)	0.85 (0.033)	D	4000	—
	0.85 (0.033)	D	4000	—
	0.85 (0.033)	D	4000	—
□MK316 (1206)	1.15 (0.045)	F	—	3000
	1.25 (0.049)	G	—	3000
	1.6 (0.063)	L	—	2000
□MK325 (1210)	0.85 (0.033)	D	—	2000
	1.15 (0.045)	F		
	1.5 (0.059)	H		
	1.9 (0.075)	N		
	2.0max (0.079)	Y	—	2000
□MK432 (1812)	2.5 (0.098)	M	—	500 (T), 1000 (P)
	2.5 (0.098)	M	—	500


②テーピング材質 Taping material

紙テープ
Card board carrier tape


※プレスポケットタイプは、
ボトムテープ無し。



エンボステープ Embossed Tape




③バルクカセット Bulk Cassette




105, 107, 212形状で個別対応致しますのでお問い合わせ下さい。
Please contact any of our offices for accepting your requirement according to dimensions 0402, 0603, 0805.(inch)

③テーピング寸法 Taping dimensions 紙テープ Paper Tape (8mm幅) (0.315inches wide)




Type (EIA)	チップ挿入部 Chip Cavity		挿入ピッチ Insertion Pitch	テープ厚み Tape Thickness	
	A	B		T	T1
□MK042 (01005)	0.25 (0.010)	0.45 (0.018)	2.0 ± 0.05 (0.079 ± 0.002)	0.36max. (0.014)	0.27max. (0.011)
□MK063 (0201)	0.37 (0.016)	0.67 (0.027)	2.0 ± 0.05 (0.079 ± 0.002)	0.45max. (0.018)	0.42max. (0.017)
□WK105 (0204)	0.65 (0.026)	1.15 (0.045)	2.0 ± 0.05 (0.079 ± 0.002)	0.45max. (0.018max)	0.42max. (0.017max)

Unit : mm (inch)



Type (EIA)	チップ挿入部 Chip Cavity		挿入ピッチ Insertion Pitch	テープ厚み Tape Thickness	
	A	B		T	
□2K096 (0302)	0.72 (0.028)	1.02 (0.040)	2.0 ± 0.05 (0.079 ± 0.002)	0.45max.(0.018max) 0.6max.(0.024max)	
□MK105 (0402)	0.65 (0.026)	1.15 (0.045)	2.0 ± 0.05 (0.079 ± 0.002)	0.8max. (0.031max.)	
□VK105 (0402)					


Unit : mm (inch)



Type (EIA)	チップ挿入部 Chip Cavity		挿入ピッチ Insertion Pitch	テープ厚み Tape Thickness	
	A	B		T	
□MK107 (0603)	1.0 (0.039)	1.8 (0.071)	4.0 ± 0.1 (0.157 ± 0.004)	1.1max. (0.043max.)	
□WK107 (0306)					
□2K110 (0504)	1.15 (0.045)	1.55 (0.061)	4.0 ± 0.1 (0.157 ± 0.004)	1.0max. (0.039max.)	
□MK212 (0805)	1.65 (0.065)	2.4 (0.094)	4.0 ± 0.1 (0.157 ± 0.004)	1.1max. (0.043max.)	
□WK212 (0508)					
□4K212 (0805)					
□2K212 (0805)					
□MK316 (1206)	2.0 (0.079)	3.6 (0.142)			

Unit : mm (inch)


エンボステープ Embossed tape (8mm幅) (0.315inches wide)



Type (EIA)	チップ挿入部 Chip cavity		挿入ピッチ Insertion Pitch	テープ厚み Tape Thickness	
	A	B		K	T
□WK107 (0306)	1.0 (0.039)	1.8 (0.071)	4.0 ± 0.1 (0.157 ± 0.004)	1.3max. (0.051max.)	0.25 ± 0.1 (0.01 ± 0.004)
□MK212 (0805)	1.65 (0.065)	2.4 (0.094)			
□MK316 (1206)	2.0 (0.079)	3.6 (0.142)		3.4max. (0.134max.)	0.6max. (0.024max.)
□MK325 (1210)	2.8 (0.110)	3.6 (0.142)			

Unit : mm (inch)


エンボステープ Embossed tape (12mm幅) (0.472inches wide)




Type (EIA)	チップ挿入部 Chip cavity		挿入ピッチ Insertion Pitch	テープ厚み Tape Thickness	
	A	B		K	T
□MK432 (1812)	3.7 (0.146)	4.9 (0.193)	8.0 ± 0.1 (0.315 ± 0.004)	4.0max. (0.157max.)	0.6max. (0.024max.)

Unit : mm (inch)

④ リーダー部／空部 Leader and Blank portion




⑤ リール寸法 Reel size




⑥ トップテープ強度 Top Tape Strength



トップテープのはがし力とは図矢印方向にて0.1～0.7Nとなります。
The top tape requires a peel-off force of 0.1～0.7N in the direction of the arrow as illustrated below.



Multilayer Ceramic Capacitor Chips

Item		Specified Value			Test Methods and Remarks	
		Temperature Compensating (Class 1)		High Permittivity (Class 2)		
		Standard	High Frequency Type	Standard Note1		High Value
1.Operating Temperature Range		-55 to +125℃		BJ : -55 to +125℃ F : -25 to +85℃	-25 to +85℃	High Capacitance Type BJ (X7R) : -55~+125℃, BJ (X5R) : -55~+85℃ E (Y5U) : -30~+85℃, F (Y5V) : -30~+85℃
2.Storage Temperature Range		-55 to +125℃		BJ : -55 to +125℃ F : -25 to +85℃	-25 to +85℃	High Capacitance Type BJ (X7R) : -55~+125℃, BJ (X5R) : -55~+85℃ E (Y5U) : -30~+85℃, F (Y5V) : -30~+85℃
3.Rated Voltage		50VDC,25VDC, 16VDC	16VDC 50VDC	50VDC,25VDC	50VDC,35VDC,25VDC 16VDC,10VDC,6.3VDC 4DVC, 2.5VDC	
4.Withstanding Voltage Between terminals		No breakdown or damage	No abnormality	No breakdown or damage		Applied voltage: Rated voltage×3 (Class 1) Rated voltage×2.5 (Class 2) Duration: 1 to 5 sec. Charge/discharge current: 50mA max. (Class 1,2)
5.Insulation Resistance		10000 MΩ min.		500 MΩ μF. or 10000 MΩ., whichever is the smaller. Note 5		Applied voltage: Rated voltage Duration: 60±5 sec. Charge/discharge current: 50mA max.
6.Capacitance (Tolerance)		0.5 to 5 pF: ±0.25 pF 1 to 10pF: ±0.5 pF 5 to 10 pF: ±1 pF 11 pF or over: ± 5% ±10% 105TYPE [△] ,S [△] ,T [△] ,U [△] only 0.5~2pF: ±0.1pF 2.2~20pF: ±5%	0.5 to 2 pF : ±0.1 pF 2.2 to 5.1 pF : ±5%	BJ: ±10%, ±20% F : +80% -20%	BJ : ±10%、±20% F : -20%／+80%	Measuring frequency : Class1 : 1MHz±10% (C≤1000pF) 1 k Hz±10% (C>1000pF) Class2 : 1 k Hz±10% (C≤10 μF) 120Hz±10Hz (C>10 μF) Measuring voltage : Note 4 Class1 : 0.5~5Vrms (C≤1000pF) 1±0.2Vrms (C>1000pF) Class2 : 1±0.2Vrms (C≤10 μF) 0.5±0.1Vrms (C>10 μF) Bias application: None
7.Q or Tangent of Loss Angle (tan δ)		Under 30 pF : Q≥400 + 20C 30 pF or over : Q≥1000 C= Nominal capacitance	Refer to detailed specification	BJ: 2.5% max. (50V, 25V) F: 5.0% max. (50V, 25V) Note 4	BJ : 2.5% max. F : 7% max. Note 4	Multilayer: Measuring frequency : Class1 : 1MHz±10% (C≤1000pF) 1 k Hz±10% (C>1000pF) Class2 : 1 k Hz±10% (C≤10 μF) 120Hz±10Hz (C>10 μF) Measuring voltage : Note 4 Class1 : 0.5~5Vrms (C≤1000pF) 1±0.2Vrms (C>1000pF) Class2 : 1±0.2Vrms (C≤10 μF) 0.5±0.1Vrms (C>10 μF) Bias application: None High—Frequency—Multilayer: Measuring frequency: 1GHz Measuring equipment: HP4291A Measuring jig: HP16192A
8.Temperature Characteristic of Capacitance	(Without voltage application)	CK : 0±250 CJ : 0±120 CH : 0±60 CG : 0±30 RH : -220±60 SK : -330±250 SJ : -330±120 SH : -330±60 TK : -470±250 TJ : -470±120 UK : -750±250 UJ : -750±120 SL : +350 to -1000 (ppm/℃)	CH : 0±60 RH : -220±60 (ppm/℃)	BJ : ±10% (-25~85℃) F : +30% (-25~85℃) -80 BJ (X7R) : ±15% F (Y5V) : +22% -82	BJ : ±10% (-25~+85℃) F : +30%／-80% (-25~+85℃) BJ (X7R, X5R) : ±15% F (Y5V) : +22%／-82%	According to JIS C 5102 clause 7.12. Temperature compensating: Measurement of capacitance at 20℃ and 85℃ shall be made to calculate temperature characteristic by the following equation. $\frac{(C_{85}-C_{20})}{C_{20} \times \Delta T} \times 10^6 \text{ (ppm/℃)}$ High permittivity: Change of maximum capacitance deviation in step 1 to 5 Temperature at step 1: +20℃ Temperature at step 2: minimum operating temperature Temperature at step 3: +20℃ (Reference temperature) Temperature at step 4: maximum operating temperature Temperature at step 5: +20℃ Reference temperature for X7R, X5R, Y5U and Y5V shall be +25℃
9.Resistance to Flexure of Substrate		Appearance: No abnormality Capacitance change: Within ±5% or ±0.5 pF, whichever is larger.	Appearance: No abnormality Capacitance change: Within±0.5 pF	Appearance: No abnormality Capacitance change: BJ : Within ±12.5% F : Within ±30%		Warp: 1mm Testing board: glass epoxy—resin substrate Thickness: 1.6mm (063 TYPE : 0.8mm) The measurement shall be made with board in the bent position.  (Unit: mm)

Multilayer Ceramic Capacitor Chips

Item	Specified Value				Test Methods and Remarks
	Temperature Compensating (Class 1)		High Permittivity (Class 2)		
	Standard	High Frequency Type	Standard Note1	High Value	
10.Body Strength	—	No mechanical damage.	—	—	High Frequency Multilayer: Applied force: 5N Duration: 10 sec. 
11.Adhesion of Electrode	No separation or indication of separation of electrode.				Applied force: 5N (01005, 0201, 0302 TYPE 2N) Duration: 30±5 sec. 
12.Solderability	At least 95% of terminal electrode is covered by new solder.				Solder temperature: 230±5°C Duration: 4±1 sec.
13.Resistance to soldering	Appearance: No abnormality Capacitance change: Within ±2.5% or ±0.25pF, whichever is larger. Q: Initial value Insulation resistance: Initial value Withstanding voltage (between terminals): No abnormality	Appearance: No abnormality Capacitance change: Within ±2.5% Q: Initial value Insulation resistance: Initial value Withstanding voltage (between terminals): No abnormality	Appearance: No abnormality Capacitance change: Within ±7.5% (BJ) Within ±20% (F) tan δ: Initial value Note 4 Insulation resistance: Initial value Withstanding voltage (between terminals): No abnormality		Preconditioning: Thermal treatment (at 150°C for 1 hr) (Applicable to Class 2.) Solder temperature: 270±5°C Duration: 3±0.5 sec. Preheating conditions: 80 to 100°C, 2 to 5 min. or 5 to 10 min. 150 to 200°C, 2 to 5 min. or 5 to 10 min. Recovery: Recovery for the following period under the standard condition after the test. 6~24 hrs (Class 1) 24±2 hrs (Class 2)
14.Thermal shock	Appearance: No abnormality Capacitance change: Within ±2.5% or ±0.25pF, whichever is larger. Q: Initial value Insulation resistance: Initial value Withstanding voltage (between terminals): No abnormality	Appearance: No abnormality Capacitance change: Within ±0.25pF Q: Initial value Insulation resistance: Initial value Withstanding voltage (between terminals): No abnormality	Appearance: No abnormality Capacitance change: Within ±7.5% (BJ) Within ±20% (F) tan δ: Initial value Note 4 Insulation resistance: Initial value Withstanding voltage (between terminals): No abnormality		Preconditioning: Thermal treatment (at 150°C for 1 hr) (Applicable to Class 2.) Conditions for 1 cycle: Step 1: Minimum operating temperature $+0/-3$ °C 30±3 min. Step 2: Room temperature 2 to 3 min. Step 3: Maximum operating temperature $+0/-3$ °C 30±3 min. Step 4: Room temperature 2 to 3 min. Number of cycles: 5 times Recovery after the test: 6~24 hrs (Class 1) 24±2 hrs (Class 2)
15.Damp Heat (steady state)	Appearance: No abnormality Capacitance change: Within ±5% or ±0.5pF, whichever is larger. Q: $C \geq 30$ pF : $Q \geq 350$ $10 \leq C < 30$ pF: $Q \geq 275 + 2.5C$ $C < 10$ pF : $Q \geq 200 + 10C$ C: Nominal capacitance Insulation resistance: 1000 MΩ min.	Appearance: No abnormality Capacitance change: Within ±0.5pF, Insulation resistance: 1000 MΩ min.	Appearance: No abnormality Capacitance change: BJ: Within ±12.5% F: Within ±30% tan δ: BJ: 5.0% max. F: 7.5% max. Note 4 Insulation resistance: 50 MΩ μF or 1000 MΩ whichever is smaller. Note 5	Appearance: No abnormality Capacitance change: BJ: Within ±12.5% Note 4 tan δ: BJ: 5.0% max. Note 4. F: 11.0% max. Insulation resistance: 50 MΩ μF or 1000 MΩ whichever is smaller. Note 5	Multilayer : Preconditioning: Thermal treatment (at 150°C for 1 hr) (Applicable to Class 2.) Temperature: 40±2°C Humidity: 90 to 95% RH Duration: 500 $+24/-0$ hrs Recovery: Recovery for the following period under the standard condition after the removal from test chamber. 6~24 hrs (Class 1) 24±2 hrs (Class 2) High-Frequency Multilayer: Temperature: 60±2°C Humidity: 90 to 95% RH Duration: 500 $+24/-0$ hrs Recovery: Recovery for the following period under the standard condition after the removal from test chamber. 6~24 hrs (Class 1)

Multilayer Ceramic Capacitor Chips

Item	Specified Value				Test Methods and Remarks
	Temperature Compensating (Class 1)		High Permittivity (Class 2)		
	Standard	High Frequency Type	Standard Note1	High Value	
16.Loading under Damp Heat	Appearance: No abnormality Capacitance change: Within ± 7.5% or ± 0.75pF, whichever is larger. Q: C≥30 pF: Q≥200 C<30 pF: Q≥100 + 10C/3 C : Nominal capacitance Insulation resistance: 500 MΩ min.	Appearance: No abnormality Capacitance change: C≤2 pF: Within ±0.4 pF C>2 pF: Within ±0.75 pF C : Nominal capacitance Insulation resistance: 500 MΩ min.	Appearance: No abnormality Capacitance change: BJ: Within ± 12.5% F: Within ±30% Note 4 tan δ: BJ: 5.0% max. F: 7.5% max. Note 4 Insulation resistance: 25 MΩ μF or 500 MΩ, whichever is the smaller. Note 5	Appearance: No abnormality Capacitance change: BJ : Within±12.5% F : Within±30% Note 4 tan δ : BJ : 5.0%max. F : 11%max. Note 4 Insulation resistance: 25 MΩ μF or 500 MΩ, whichever is the smaller. Note 5	According to JIS C 5102 Clause 9. 9. Multilayer: Preconditioning: Voltage treatment (Class 2) Temperature: 40±2℃ Humidity: 90 to 95% RH Duration: 500 ⁺²⁴ ₋₀ hrs Applied voltage: Rated voltage Charge and discharge current: 50mA max. (Class 1,2) Recovery: Recovery for the following period under the standard condition after the removal from test chamber. 6~24 hrs (Class 1) 24±2 hrs (Class 2) High—Frequency Multilayer: Temperature: 60±2℃ Humidity: 90 to 95% RH Duration: 500 ⁺²⁴ ₋₀ hrs Applied voltage: Rated voltage Charge and discharge current: 50mA max. Recovery: 6~24 hrs of recovery under the standard condition after the removal from test chamber.
17.Loading at High Temperature	Appearance: No abnormality Capacitance change: Within ±3% or ±0.3pF, whichever is larger. Q: C≥30 pF : Q≥350 10≤C<30 pF: Q≥275 + 2.5C C<10 pF: Q≥200 + 10C C : Nominal capacitance Insulation resistance: 1000 MΩ min.	Appearance: No abnormality Capacitance change: Within ±3% or ± 0.3pF, whichever is larger. Insulation resistance: 1000 MΩ min.	Appearance: No abnormality Capacitance change: BJ: Within ± 12.5% F: Within ±30% Note 4 tan δ: BJ: 4.0% max. F: 7.5% max. Note 4 Insulation resistance: 50 MΩ μF or 1000 MΩ, whichever is smaller. Note 5	Appearance: No abnormality Capacitance change: BJ : Within ±12.5% Within ±20%※※ Within ±25%※※ F : Within±30% Note 4 tan δ : BJ : 5.0%max. F : 11%max. Note 4 Insulation resistance: 50 MΩ μF or 1000 MΩ, whichever is smaller. Note 5	According to JIS C 5102 clause 9.10. Multilayer: Preconditioning: Voltage treatment (Class 2) Temperature:125±3℃ (Class 1, Class 2: B, BJ (X7R)) 85±2℃ (Class 2: BJ,F) Duration: 1000 ⁺⁴⁸ ₋₀ hrs Applied voltage: Rated voltage×2 Note 6 Recovery: Recovery for the following period under the standard condition after the removal from test chamber. 6~24 hrs (Class 1) 24±2 hrs (Class 2) High—Frequency Multilayer: Temperature: 125±3℃ (Class 1) Duration: 1000 ⁺⁴⁸ ₋₀ hrs Applied voltage: Rated voltage×2 Recovery: 6~24 hrs of recovery under the standard condition after the removal from test chamber.



Note 1 :For 105 type, specified in "High value".

Note 2 :Thermal treatment (Multilayer): 1 hr of thermal treatment at $150 \pm 0 / -10^\circ\text{C}$ followed by 24 ± 2 hrs of recovery under the standard condition shall be performed before the measurement.Note 3 :Voltage treatment (Multilayer): 1 hr of voltage treatment under the specified temperature and voltage for testing followed by 24 ± 2 hrs of recovery under the standard condition shall be performed before the measurement.

































Note 4, 5 :The figure indicates typical inspection. Please refer to individual specifications.

Note 6 :Some of the parts are applicable in rated voltage $\times 1.5$. Please refer to individual specifications.Note on standard condition: "standard condition" referred to herein is defined as follows: 5 to 35°C of temperature, 45 to 85% relative humidity, and 86 to 106kPa of air pressure.When there are questions concerning measurement results: In order to provide correlation data, the test shall be conducted under condition of $20 \pm 2^\circ\text{C}$ of temperature, 60 to 70% relative humidity, and 86 to 106kPa of air pressure. Unless otherwise specified, all the tests are conducted under the "standard condition."















Precautions on the use of Multilayer Ceramic Capacitors

Stages	Precautions	Technical considerations																																																																																																																																		
1.Circuit Design	Verification of operating environment, electrical rating and performance 1. A malfunction in medical equipment, spacecraft, nuclear reactors, etc. may cause serious harm to human life or have severe social ramifications. As such, any capacitors to be used in such equipment may require higher safety and/or reliability considerations and should be clearly differentiated from components used in general purpose applications. Operating Voltage (Verification of Rated voltage) 1. The operating voltage for capacitors must always be lower than their rated values. If an AC voltage is loaded on a DC voltage, the sum of the two peak voltages should be lower than the rated value of the capacitor chosen. For a circuit where both an AC and a pulse voltage may be present, the sum of their peak voltages should also be lower than the capacitor's rated voltage. 2. Even if the applied voltage is lower than the rated value, the reliability of capacitors might be reduced if either a high frequency AC voltage or a pulse voltage having rapid rise time is present in the circuit.																																																																																																																																			
2.PCB Design	Pattern configurations (Design of Land-patterns) 1. When capacitors are mounted on a PCB, the amount of solder used (size of fillet) can directly affect capacitor performance. Therefore, the following items must be carefully considered in the design of solder land patterns: (1) The amount of solder applied can affect the ability of chips to withstand mechanical stresses which may lead to breaking or cracking. Therefore, when designing land-patterns it is necessary to consider the appropriate size and configuration of the solder pads which in turn determines the amount of solder necessary to form the fillets. (2) When more than one part is jointly soldered onto the same land or pad, the pad must be designed so that each component's soldering point is separated by solder-resist.	1.The following diagrams and tables show some examples of recommended patterns to prevent excessive solder amounts. (larger fillets which extend above the component end terminations) Examples of improper pattern designs are also shown. (1) Recommended land dimensions for a typical chip capacitor land patterns for PCBs  Recommended land dimensions for wave-soldering (unit: mm) <table><tr><th>Type</th><th>107</th><th>212</th><th>316</th><th>325</th></tr><tr><td rowspan="2">Size</td><td>L</td><td>1.6</td><td>2.0</td><td>3.2</td><td>3.2</td></tr><tr><td>W</td><td>0.8</td><td>1.25</td><td>1.6</td><td>2.5</td></tr><tr><td>A</td><td>0.8~1.0</td><td>1.0~1.4</td><td>1.8~2.5</td><td>1.8~2.5</td></tr><tr><td>B</td><td>0.5~0.8</td><td>0.8~1.5</td><td>0.8~1.7</td><td>0.8~1.7</td></tr><tr><td>C</td><td>0.6~0.8</td><td>0.9~1.2</td><td>1.2~1.6</td><td>1.8~2.5</td></tr></table> Recommended land dimensions for reflow-soldering (unit: mm) <table><tr><th>Type</th><th>042</th><th>063</th><th>105</th><th>107</th><th>212</th><th>316</th><th>325</th><th>432</th></tr><tr><td rowspan="2">Size</td><td>L</td><td>0.4</td><td>0.6</td><td>1.0</td><td>1.6</td><td>2.0</td><td>3.2</td><td>3.2</td><td>4.5</td></tr><tr><td>W</td><td>0.2</td><td>0.3</td><td>0.5</td><td>0.8</td><td>1.25</td><td>1.6</td><td>2.5</td><td>3.2</td></tr><tr><td>A</td><td>0.15~0.25</td><td>0.20~0.30</td><td>0.45~0.55</td><td>0.8~1.0</td><td>0.8~1.2</td><td>1.8~2.5</td><td>1.8~2.5</td><td>2.5~3.5</td></tr><tr><td>B</td><td>0.10~0.20</td><td>0.20~0.30</td><td>0.40~0.50</td><td>0.6~0.8</td><td>0.8~1.2</td><td>1.0~1.5</td><td>1.0~1.5</td><td>1.5~1.8</td></tr><tr><td>C</td><td>0.15~0.30</td><td>0.25~0.40</td><td>0.45~0.55</td><td>0.6~0.8</td><td>0.9~1.6</td><td>1.2~2.0</td><td>1.8~3.2</td><td>2.3~3.5</td></tr></table> Excess solder can affect the ability of chips to withstand mechanical stresses. Therefore, please take proper precautions when designing land-patterns.  <table><tr><th>Type</th><th>212 (4 circuits)</th></tr><tr><td rowspan="2">Size</td><td>L</td><td>2.0</td></tr><tr><td>W</td><td>1.25</td></tr><tr><td>a</td><td>0.5~0.6</td></tr><tr><td>b</td><td>0.5~0.6</td></tr><tr><td>c</td><td>0.2~0.3</td></tr><tr><td>d</td><td>0.5</td></tr></table> <table><tr><th>Type</th><th>212 (2 circuits)</th><th>110 (2 circuits)</th><th>096 (2 circuits)</th></tr><tr><td rowspan="2">Size</td><td>L</td><td>2.0</td><td>1.37</td><td>0.9</td></tr><tr><td>W</td><td>1.25</td><td>1.0</td><td>0.6</td></tr><tr><td>a</td><td>0.5~0.6</td><td>0.35~0.45</td><td>0.25~0.35</td></tr><tr><td>b</td><td>0.5~0.6</td><td>0.55~0.65</td><td>0.15~0.25</td></tr><tr><td>c</td><td>0.5~0.6</td><td>0.3~0.4</td><td>0.15~0.25</td></tr><tr><td>d</td><td>1.0</td><td>0.64</td><td>0.45</td></tr></table>	Type	107	212	316	325	Size	L	1.6	2.0	3.2	3.2	W	0.8	1.25	1.6	2.5	A	0.8~1.0	1.0~1.4	1.8~2.5	1.8~2.5	B	0.5~0.8	0.8~1.5	0.8~1.7	0.8~1.7	C	0.6~0.8	0.9~1.2	1.2~1.6	1.8~2.5	Type	042	063	105	107	212	316	325	432	Size	L	0.4	0.6	1.0	1.6	2.0	3.2	3.2	4.5	W	0.2	0.3	0.5	0.8	1.25	1.6	2.5	3.2	A	0.15~0.25	0.20~0.30	0.45~0.55	0.8~1.0	0.8~1.2	1.8~2.5	1.8~2.5	2.5~3.5	B	0.10~0.20	0.20~0.30	0.40~0.50	0.6~0.8	0.8~1.2	1.0~1.5	1.0~1.5	1.5~1.8	C	0.15~0.30	0.25~0.40	0.45~0.55	0.6~0.8	0.9~1.6	1.2~2.0	1.8~3.2	2.3~3.5	Type	212 (4 circuits)	Size	L	2.0	W	1.25	a	0.5~0.6	b	0.5~0.6	c	0.2~0.3	d	0.5	Type	212 (2 circuits)	110 (2 circuits)	096 (2 circuits)	Size	L	2.0	1.37	0.9	W	1.25	1.0	0.6	a	0.5~0.6	0.35~0.45	0.25~0.35	b	0.5~0.6	0.55~0.65	0.15~0.25	c	0.5~0.6	0.3~0.4	0.15~0.25	d	1.0	0.64	0.45
Type	107	212	316	325																																																																																																																																
Size	L	1.6	2.0	3.2	3.2																																																																																																																															
	W	0.8	1.25	1.6	2.5																																																																																																																															
A	0.8~1.0	1.0~1.4	1.8~2.5	1.8~2.5																																																																																																																																
B	0.5~0.8	0.8~1.5	0.8~1.7	0.8~1.7																																																																																																																																
C	0.6~0.8	0.9~1.2	1.2~1.6	1.8~2.5																																																																																																																																
Type	042	063	105	107	212	316	325	432																																																																																																																												
Size	L	0.4	0.6	1.0	1.6	2.0	3.2	3.2	4.5																																																																																																																											
	W	0.2	0.3	0.5	0.8	1.25	1.6	2.5	3.2																																																																																																																											
A	0.15~0.25	0.20~0.30	0.45~0.55	0.8~1.0	0.8~1.2	1.8~2.5	1.8~2.5	2.5~3.5																																																																																																																												
B	0.10~0.20	0.20~0.30	0.40~0.50	0.6~0.8	0.8~1.2	1.0~1.5	1.0~1.5	1.5~1.8																																																																																																																												
C	0.15~0.30	0.25~0.40	0.45~0.55	0.6~0.8	0.9~1.6	1.2~2.0	1.8~3.2	2.3~3.5																																																																																																																												
Type	212 (4 circuits)																																																																																																																																			
Size	L	2.0																																																																																																																																		
	W	1.25																																																																																																																																		
a	0.5~0.6																																																																																																																																			
b	0.5~0.6																																																																																																																																			
c	0.2~0.3																																																																																																																																			
d	0.5																																																																																																																																			
Type	212 (2 circuits)	110 (2 circuits)	096 (2 circuits)																																																																																																																																	
Size	L	2.0	1.37	0.9																																																																																																																																
	W	1.25	1.0	0.6																																																																																																																																
a	0.5~0.6	0.35~0.45	0.25~0.35																																																																																																																																	
b	0.5~0.6	0.55~0.65	0.15~0.25																																																																																																																																	
c	0.5~0.6	0.3~0.4	0.15~0.25																																																																																																																																	
d	1.0	0.64	0.45																																																																																																																																	

Precautions on the use of Multilayer Ceramic Capacitors

Stages	Precautions	Technical considerations																																														
2.PCB Design	Pattern configurations (Capacitor layout on panelized [breakaway] PC boards) 1. After capacitors have been mounted on the boards, chips can be subjected to mechanical stresses in subsequent manufacturing processes (PCB cutting, board inspection, mounting of additional parts, assembly into the chassis, wave soldering the reflow soldered boards etc.) For this reason, planning pattern configurations and the position of SMD capacitors should be carefully performed to minimize stress.	LWDC Recommended land dimensions for reflow-soldering  <table><tr><th>Type</th><th>105</th><th>107</th><th>212</th></tr><tr><td rowspan="2">Size</td><td>L</td><td>0.52</td><td>0.8</td><td>1.25</td></tr><tr><td>W</td><td>1.0</td><td>1.6</td><td>2.0</td></tr><tr><td>A</td><td>0.18~0.22</td><td>0.25~0.3</td><td>0.5~0.7</td></tr><tr><td>B</td><td>0.2~0.25</td><td>0.3~0.4</td><td>0.4~0.5</td></tr><tr><td>C</td><td>0.9~1.1</td><td>1.5~1.7</td><td>1.9~2.1</td></tr></table> (unit: mm) (2) Examples of good and bad solder application <table><tr><th>Items</th><th>Not recommended</th><th>Recommended</th></tr><tr><td>Mixed mounting of SMD and leaded components</td><td></td><td></td></tr><tr><td>Component placement close to the chassis</td><td></td><td></td></tr><tr><td>Hand-soldering of leaded components near mounted components</td><td></td><td></td></tr><tr><td>Horizontal component placement</td><td></td><td></td></tr></table> 1-1. The following are examples of good and bad capacitor layout; SMD capacitors should be located to minimize any possible mechanical stresses from board warp or deflection. <table><tr><th></th><th>Not recommended</th><th>Recommended</th></tr><tr><td>Deflection of the board</td><td></td><td></td></tr></table> 1-2. To layout the capacitors for the breakaway PC board, it should be noted that the amount of mechanical stresses given will vary depending on capacitor layout. The example below shows recommendations for better design.  1-3. When breaking PC boards along their perforations, the amount of mechanical stress on the capacitors can vary according to the method used. The following methods are listed in order from least stressful to most stressful: push-back, slit, V-grooving, and perforation. Thus, any ideal SMD capacitor layout must also consider the PCB splitting procedure.	Type	105	107	212	Size	L	0.52	0.8	1.25	W	1.0	1.6	2.0	A	0.18~0.22	0.25~0.3	0.5~0.7	B	0.2~0.25	0.3~0.4	0.4~0.5	C	0.9~1.1	1.5~1.7	1.9~2.1	Items	Not recommended	Recommended	Mixed mounting of SMD and leaded components			Component placement close to the chassis			Hand-soldering of leaded components near mounted components			Horizontal component placement				Not recommended	Recommended	Deflection of the board		
		Type	105	107	212																																											
Size	L	0.52	0.8	1.25																																												
	W	1.0	1.6	2.0																																												
A	0.18~0.22	0.25~0.3	0.5~0.7																																													
B	0.2~0.25	0.3~0.4	0.4~0.5																																													
C	0.9~1.1	1.5~1.7	1.9~2.1																																													
Items	Not recommended	Recommended																																														
Mixed mounting of SMD and leaded components																																																
Component placement close to the chassis																																																
Hand-soldering of leaded components near mounted components																																																
Horizontal component placement																																																
	Not recommended	Recommended																																														
Deflection of the board																																																



Precautions on the use of Multilayer Ceramic Capacitors

Stages	Precautions	Technical considerations																	
3.Considerations for auto-matic placement	Adjustment of mounting machine 1. Excessive impact load should not be imposed on the capacitors when mounting onto the PC boards. 2. The maintenance and inspection of the mounters should be conducted periodically. Selection of Adhesives 1. Mounting capacitors with adhesives in preliminary assembly, before the soldering stage, may lead to degraded capacitor characteristics unless the following factors are appropriately checked; the size of land patterns, type of adhesive, amount applied, hardening temperature and hardening period. Therefore, it is imperative to consult the manufacturer of the adhesives on proper usage and amounts of adhesive to use.	1. If the lower limit of the pick-up nozzle is low, too much force may be imposed on the capacitors, causing damage. To avoid this, the following points should be considered before lowering the pick-up nozzle: (1) The lower limit of the pick-up nozzle should be adjusted to the surface level of the PC board after correcting for deflection of the board. (2) The pick-up pressure should be adjusted between 1 and 3 N static loads. (3) To reduce the amount of deflection of the board caused by impact of the pick-up nozzle, supporting pins or back-up pins should be used under the PC board. The following diagrams show some typical examples of good pick-up nozzle placement: <table><tr><th></th><th>Not recommended</th><th>Recommended</th></tr><tr><td>Single-sided mounting</td><td></td><td></td></tr><tr><td>Double-sided mounting</td><td></td><td></td></tr></table> 2. As the alignment pin wears out, adjustment of the nozzle height can cause chipping or cracking of the capacitors because of mechanical impact on the capacitors. To avoid this, the monitoring of the width between the alignment pin in the stopped position, and maintenance, inspection and replacement of the pin should be conducted periodically. 5. Some adhesives may cause reduced insulation resistance. The difference between the shrinkage percentage of the adhesive and that of the capacitors may result in stresses on the capacitors and lead to cracking. Moreover, too little or too much adhesive applied to the board may adversely affect component placement, so the following precautions should be noted in the application of adhesives. (1) Required adhesive characteristics a. The adhesive should be strong enough to hold parts on the board during the mounting & solder process. b. The adhesive should have sufficient strength at high temperatures. c. The adhesive should have good coating and thickness consistency. d. The adhesive should be used during its prescribed shelf life. e. The adhesive should harden rapidly f. The adhesive must not be contaminated. g. The adhesive should have excellent insulation characteristics. h. The adhesive should not be toxic and have no emission of toxic gasses. (2) The recommended amount of adhesives is as follows; <table><tr><th>Figure</th><th>212/316 case sizes as examples</th></tr><tr><td>a</td><td>0.3mm min</td></tr><tr><td>b</td><td>100 ~120 μ m</td></tr><tr><td>c</td><td>Adhesives should not contact the pad</td></tr></table> Amount of adhesive  After capacitors are bonded 		Not recommended	Recommended	Single-sided mounting			Double-sided mounting			Figure	212/316 case sizes as examples	a	0.3mm min	b	100 ~120 μ m	c	Adhesives should not contact the pad
	Not recommended	Recommended																	
Single-sided mounting																			
Double-sided mounting																			
Figure	212/316 case sizes as examples																		
a	0.3mm min																		
b	100 ~120 μ m																		
c	Adhesives should not contact the pad																		

Precautions on the use of Multilayer Ceramic Capacitors

Stages	Precautions	Technical considerations
4. Soldering	Selection of Flux 1. Since flux may have a significant effect on the performance of capacitors, it is necessary to verify the following conditions prior to use; (1) Flux used should be with less than or equal to 0.1 wt% (equivalent to chlorine) of halogenated content. Flux having a strong acidity content should not be applied. (2) When soldering capacitors on the board, the amount of flux applied should be controlled at the optimum level. (3) When using water-soluble flux, special care should be taken to properly clean the boards. Soldering Temperature, time, amount of solder, etc. are specified in accordance with the following recommended conditions. Sn-Zn solder paste can affect MLCC reliability performance. Please contact us prior to usage.	1-1. When too much halogenated substance (Chlorine, etc.) content is used to activate the flux, or highly acidic flux is used, an excessive amount of residue after soldering may lead to corrosion of the terminal electrodes or degradation of insulation resistance on the surface of the capacitors. 1-2. Flux is used to increase solderability in flow soldering, but if too much is applied, a large amount of flux gas may be emitted and may detrimentally affect solderability. To minimize the amount of flux applied, it is recommended to use a flux-bubbling system. 1-3. Since the residue of water-soluble flux is easily dissolved by water content in the air, the residue on the surface of capacitors in high humidity conditions may cause a degradation of insulation resistance and therefore affect the reliability of the components. The cleaning methods and the capability of the machines used should also be considered carefully when selecting water-soluble flux. 1-1. Preheating when soldering Heating: Ceramic chip components should be preheated to within 100 to 130°C of the soldering. Cooling: The temperature difference between the components and cleaning process should not be greater than 100°C. Ceramic chip capacitors are susceptible to thermal shock when exposed to rapid or concentrated heating or rapid cooling. Therefore, the soldering process must be conducted with great care so as to prevent malfunction of the components due to excessive thermal shock. Recommended conditions for soldering [Reflow soldering] Temperature profile ※ Ceramic chip components should be preheated to within 100 to 130°C of the soldering. ※ Assured to be reflow soldering for 2 times. Caution 1. The ideal condition is to have solder mass (fillet) controlled to 1/2 to 1/3 of the thickness of the capacitor, as shown below: 2. Because excessive dwell times can detrimentally affect solderability, soldering duration should be kept as close to recommended times as possible. [Wave soldering] Temperature profile ※ Ceramic chip components should be preheated to within 100 to 130°C of the soldering. ※ Assured to be wave soldering for 1 time. ※ Except for reflow soldering type. Caution 1. Make sure the capacitors are preheated sufficiently. 2. The temperature difference between the capacitor and melted solder should not be greater than 100 to 130°C 3. Cooling after soldering should be as gradual as possible. 4. Wave soldering must not be applied to the capacitors designated as for reflow soldering only.

Precautions on the use of Multilayer Ceramic Capacitors

Stages	Precautions	Technical considerations						
4. Soldering		[Hand soldering] Temperature profile   (Pb free soldering) ※ $\Delta T \leq 190^{\circ}\text{C}$ (3216Type max), $\Delta T \leq 130^{\circ}\text{C}$ (3225Type min) ※ It is recommended to use 20W soldering iron and the tip is 1φ or less. ※ The soldering iron should not directly touch the components. ※ Assured to be soldering iron for 1 time. Note: The above profiles are the maximum allowable soldering condition, therefore these profiles are not always recommended. Caution 1. Use a 20W soldering iron with a maximum tip diameter of 1.0 mm. 2. The soldering iron should not directly touch the capacitor.						
5.Cleaning	Cleaning conditions 1. When cleaning the PC board after the capacitors are all mounted, select the appropriate cleaning solution according to the type of flux used and purpose of the cleaning (e.g. to remove soldering flux or other materials from the production process.) 2. Cleaning conditions should be determined after verifying, through a test run, that the cleaning process does not affect the capacitor's characteristics.	1. The use of inappropriate solutions can cause foreign substances such as flux residue to adhere to the capacitor or deteriorate the capacitor's outer coating, resulting in a degradation of the capacitor's electrical properties (especially insulation resistance). 2. Inappropriate cleaning conditions (insufficient or excessive cleaning) may detrimentally affect the performance of the capacitors. (1) Excessive cleaning In the case of ultrasonic cleaning, too much power output can cause excessive vibration of the PC board which may lead to the cracking of the capacitor or the soldered portion, or decrease the terminal electrodes' strength. Thus the following conditions should be carefully checked; <table><tr><td>Ultrasonic output</td><td>Below 20 W/ ℓ</td></tr><tr><td>Ultrasonic frequency</td><td>Below 40 kHz</td></tr><tr><td>Ultrasonic washing period</td><td>5 min. or less</td></tr></table>	Ultrasonic output	Below 20 W/ ℓ	Ultrasonic frequency	Below 40 kHz	Ultrasonic washing period	5 min. or less
Ultrasonic output	Below 20 W/ ℓ							
Ultrasonic frequency	Below 40 kHz							
Ultrasonic washing period	5 min. or less							
6.Post cleaning processes	1. With some type of resins a decomposition gas or chemical reaction vapor may remain inside the resin during the hardening period or while left under normal storage conditions resulting in the deterioration of the capacitor's performance. 2. When a resin's hardening temperature is higher than the capacitor's operating temperature, the stresses generated by the excess heat may lead to capacitor damage or destruction. The use of such resins, molding materials etc. is not recommended.							
7.Handling	Breakaway PC boards (splitting along perforations) 1. When splitting the PC board after mounting capacitors and other components, care is required so as not to give any stresses of deflection or twisting to the board. 2. Board separation should not be done manually, but by using the appropriate devices. Mechanical considerations 1. Be careful not to subject the capacitors to excessive mechanical shocks. (1) If ceramic capacitors are dropped onto the floor or a hard surface, they should not be used. (2) When handling the mounted boards, be careful that the mounted components do not come in contact with or bump against other boards or components.							

Precautions on the use of Multilayer Ceramic Capacitors

Stages	Precautions	Technical considerations
8.Storage conditions	Storage - To maintain the solderability of terminal electrodes and to keep the packaging material in good condition, care must be taken to control temperature and humidity in the storage area. Humidity should especially be kept as low as possible. - Recommended conditions - Ambient temperature Below 30°C - Humidity Below 70% RH The ambient temperature must be kept below 40°C. Even under ideal storage conditions capacitor electrode solderability decreases as time passes, so should be used within 6 months from the time of delivery. - Ceramic chip capacitors should be kept where no chlorine or sulfur exists in the air. - The capacitance value of high dielectric constant capacitors (type 2 &3) will gradually decrease with the passage of time, so this should be taken into consideration in the circuit design. If such a capacitance reduction occurs, a heat treatment of 150°C for 1hour will return the capacitance to its initial level.	If the parts are stored in a high temperature and humidity environment, problems such as reduced solderability caused by oxidation of terminal electrodes and deterioration of taping/packaging materials may take place. For this reason, components should be used within 6 months from the time of delivery. If exceeding the above period, please check solderability before using the capacitors.