



Report No.: BST20200313695001LBR

UN 38.3

检测报告

产品名称: 锂电池组
Product Name: Li-ion Battery

委托单位: 深圳科宏健半导体照明有限公司
Consignor: Shenzhen KHJ Semiconductor Lighting Co., Ltd.

产品型号: 6S2P-18650
Product Type:

检测日期: Feb. 24, 2020 to Mar. 11, 2020
Tested Date:

发布日期: Mar. 12, 2020
Issued Date:

深圳市倍通检测股份有限公司

中国广东省深圳市南山区南头关口二路智恒战略性新兴产业园23-24栋

邮政编码: 518000

电话: 400-882-9628, 8009990305

电子邮件: christina@bst-lab.com



Report No.: BST20200313695001LBR

| | | | | | |
|--|--|--------------------------------------|---|-----------------------------------|---|
| 产品名称: Product Name: | 锂电池组 Li-ion Battery | 型号: Model: | 6S2P-18650 | | |
| 商标: Trade Mark: |  | 制造商: Manufacturer: | 深圳科宏健半导体照明有限公司 Shenzhen KHJ Semiconductor Lighting Co., Ltd. | | |
| 样品编号: Sample No.: | #1-#48 | 检验环境: Testing Condition: | 20-25° C, 45-75%R.H | | |
| 样品基本信息 Basic Information | | | | | |
| 标称电压 Nominal Voltage | 22.2V | 充电限制电压 Charge Limit Voltage | 25.2V | 额定容量/能量 Rate capacity/Energy | 4400mAh 97.68Wh |
| 标准充电电流 Standard Charge Current | 0.88A | 标准放电电流 Standard Discharge Current | 0.88A | 最大充电电流 Max. Charge Current | 4400mA |
| 最大放电电流 Max. Discharge Current | 4400mA | 充电截止电流 End Charge Current | 880mA | 放电截止电压 Final Discharge Voltage | 18V |
| 外观 Shape | <input checked="" type="checkbox"/> 近长方体 Almost cuboid <input type="checkbox"/> 近圆柱体 Almost Cylindrical | 样品尺寸 Size | 131.3×72.2×34.3 (mm) | 内部电池个数 Internal cells Count | 12Pcs |
| 测试方法和判定标准/ Test method and criterion: Recommendations on the Transport of Dangerous Goods, Manual of Test and Criteria (ST/SG/AC.10/11/Rev.6, 38.3/Amendment 1) 联合国《关于危险货物运输的建议书》第六修订版修正1, 38.3标准要求 (ST/SG/AC.10/11/Rev.6, 38.3/Amendment 1) | | | | | |
| 检验项目/ Test Item: T.1: Altitude simulation, Test T.2: Thermal test, Test T.3: Vibration, Test T.4: Shock Test T.5: External short circuit, Test T.6: Impact / Crush, Test T.7: Overcharge, Test T.8: Forced discharge | | | | | |
| 检验结论 / Conclusion: Pass 合格 <div style="text-align: right;"> (检测单位盖章/Sealed)</div> | | | | | |
| 检测: Tested by: |  | 审核: Reviewed by: |  | 批准: Approved by: |  |



一般说明 / General remark:

本报告出现的试验结果仅与试验样品有关.

The test results presented in this report relate only to the object tested.

除非全部复制，否则无试验室书面批准本报告不得部分复制.

This report shall not be reproduced, except in full, without the written approval of the Issuing testing laboratory.

可能的试验情况判定 / Possible test case verdicts:

| | |
|---|------------|
| — 试验情况不适用本试验产品 — Test case does not apply to the test object | N/A (or N) |
| — 试验样品满足要求 — Test object does meet the requirement | P (Pass) |
| — 试验样品不满足要求 — Test object does not meet the requirement | F (Fail) |



Report No.: BST20200313695001LBR

ST/SG/AC.10/11/Rev.6, 38.3/Amendment 1

| 条款/Clause | 标准要求/ Requirement + Test | 结果 / Result | 判定/ Verdict |
|-----------|--------------------------|-------------|-------------|
|-----------|--------------------------|-------------|-------------|

| | | | |
|-----------------|---|--|----------|
| 38.3.4.1 | Test T.1: Altitude simulation/高度模拟 | | P |
| | Test cells and batteries shall be stored at a pressure of 11.6 kPa or less for at least six hours at ambient temperature (20±5°C)/将电芯和电池在温度为20±5°C、大气压力不大于11.6kpa的环境中贮存不少于6个小时。 | | P |
| | Cells and batteries meet this requirement if there is no mass loss, no leakage, no venting, no disassembly, no rupture and no fire and if the open circuit voltage of each test cell or battery after testing is not less than 90% of its voltage immediately prior to this procedure. The requirement relating to voltage is not applicable to test cells and batteries at fully discharged states. /电芯和电池符合要求：无质量损失、无漏液、无冒烟、无分解、无破裂以及无着火现象；电芯或电池测试后的开路电压不低于测试前开路电压的90%。此项关于电压方面的要求不适用于完全放电后的电芯和电池。 | | P |
| 38.3.4.2 | Test T.2: Thermal test/温度试验 | | P |
| | Test cells and batteries are to be stored for at least six hours at a test temperature equal to 72±2°C, followed by storage for at least six hours at a test temperature equal to -40±2°C. The maximum time interval between test temperature extremes is 30 minutes. This procedure is to be repeated 10 times, after which all test cells and batteries are to be stored for 24 hours at ambient temperature (20±5°C). /首先将样品放在72±2°C的环境中放置至少6个小时，然后放在-40±2°C的环境中放置至少6个小时。温度转换的最大间隔时间为30分钟。如此循环10次，最后将样品放在20±5°C的环境中静置24小时。 | | P |
| | For large cells and batteries the duration of exposure to the test temperature extremes should be at least 12 hours. /对于大电芯，在高温和低温中放置的时间最少12个小时。 | | P |



Report No.: BST20200313695001LBR

| ST/SG/AC.10/11/Rev.6, 38.3/Amendment 1 | | | |
|--|--|-------------|-------------|
| 条款/Clause | 标准要求/ Requirement + Test | 结果 / Result | 判定/ Verdict |
| | <p>Cells and batteries meet this requirement if there is no mass loss, no leakage, no venting, no disassembly, no rupture and no fire and if the open circuit voltage of each test cell or battery after testing is not less than 90% of its voltage immediately prior to this procedure. The requirement relating to voltage is not applicable to test cells and batteries at fully discharged states.</p> <p>/电芯和电池符合要求：无质量损失、无漏液、无冒烟、无分解、无破裂以及无着火现象；电芯或电池测试后的开路电压不低于测试前开路电压的90%。此项关于电压方面的要求不适用于完全放电后的电芯和电池。</p> | | P |
| 38.3.4.3 | Test T.3: Vibration/振动 | | P |
| | <p>Cells and batteries are firmly secured to the platform of the vibration machine without distorting the cells in such a manner as to faithfully transmit the vibration. The vibration shall be a sinusoidal waveform with a logarithmic sweep between 7 Hz and 200 Hz and back to 7 Hz traversed in 15 minutes. This cycle shall be repeated 12 times for a total of 3 hours for each of three mutually perpendicular mounting positions of the cell. One of the directions of vibration must be perpendicular to the terminal face. /样品必须牢固地安装在振动台台面上。振动以正弦波形式，以7Hz增加至200Hz，然后减少回到7Hz为一个循环，一个循环持续15分钟。对样品从三个互相垂直的方向上循环12次，共3个小时。其中一个振动方向必须是垂直样品的极性平面。</p> | | P |
| | <p>The logarithmic frequency sweep shall differ for cells and batteries with a gross mass of not more than 12 kg (cells and small batteries), and for batteries with a gross mass of more than 12 kg (large batteries). /对于质量不大于12kg的样品(电芯和小电池)和质量超过12kg的电池(大电池)，对数扫频不同。</p> | | P |



Report No.: BST20200313695001LBR

ST/SG/AC.10/11/Rev.6, 38.3/Amendment 1

| 条款/Clause | 标准要求/ Requirement + Test | 结果 / Result | 判定/ Verdict |
|-----------|--|-------------|-------------|
| | For cells and small batteries: from 7 Hz a peak acceleration of 1 gn is maintained until 18 Hz is reached. The amplitude is then maintained at 0.8 mm (1.6 mm total excursion) and the frequency increased until a peak acceleration of 8 gn occurs (approximately 50 Hz). A peak acceleration of 8 gn is then maintained until the frequency is increased to 200 Hz. /对于电芯和小电池，对数扫频为：从7Hz开始保持1gn的最大加速度直到频率为18Hz，然后将振幅保持在0.8mm (总偏移1.6mm) 并增加频率直到最大加速度达到8gn (频率约为50Hz)，将最大加速度保持在8gn直到频率增加到200Hz。 | | N/A |
| | For large batteries: from 7 Hz to a peak acceleration of 1 gn is maintained until 18 Hz is reached. The amplitude is then maintained at 0.8 mm (1.6 mm total excursion) and the frequency increased until a peak acceleration of 2 gn occurs (approximately 25 Hz). A peak acceleration of 2 gn is then maintained until the frequency is increased to 200 Hz. /对于大电池，对数扫频为：从7Hz开始保持1gn的最大加速度直到频率为18Hz，然后将振幅保持在0.8mm (总偏移1.6mm) 并增加频率直到最大加速度达到2gn (频率约为25Hz)，将最大加速度保持在2gn直到频率增加到200Hz。 | | P |
| | Cells and batteries meet this requirement if there is no leakage, no venting, no disassembly, no rupture and no fire during the test and after the test and if the open circuit voltage of each test cell or battery directly after testing in its third perpendicular mounting position is not less than 90% of its voltage immediately prior to this procedure. The requirement relating to voltage is not applicable to test cells and batteries at fully discharged states./电芯和电池符合要求：无质量损失、无漏液、无冒烟、无分解、无破裂以及无着火现象；电芯或电池测试后的开路电压不低于测试前开路电压的90%。此项关于电压方面的要求不适用于完全放电后的电芯和电池。 | | P |
| 38.3.4.4 | Test T.4: Shock/冲击 | | P |



Report No.: BST20200313695001LBR

Report No.: DG120200010000001

| ST/SG/AC.10/11/Rev.6, 38.3/Amendment 1 | | | | | | | | | | | | | |
|--|--|----------------|---------------------------|----------------|-----------------|---|------|---|-----------------|---|-------|--|---|
| 条款/Clause | 标准要求/ Requirement + Test | 结果 / Result | 判定/ Verdict | | | | | | | | | | |
| | <p>Test cells and batteries shall be secured to the testing machine by means of a rigid mount which will support all mounting surfaces of each test battery.</p> <p>Each cell shall be subjected to a half-sine shock of peak acceleration of 150 gn and pulse duration of 6 milliseconds. Alternatively, large cells may be subjected to a half-sine shock of peak acceleration of 50 gn and pulse duration of 11 milliseconds.</p> <p>Each battery shall be subjected to a half-sine shock of peak acceleration depending on the mass of the battery. The pulse duration shall be 6 milliseconds for small batteries and 11 milliseconds for large batteries. The formulas below are provided to calculate the appropriate minimum peak accelerations. /以稳固的托架固定住每个电池/电芯样品，每个样品应该经受峰值加速度为150gn以及脉冲持续时间为6ms的半正弦冲击，另外，大型电池/电芯应该经受峰值加速度为50gn以及脉冲持续时间为11ms的半正弦冲击。</p> <p>每一个电池将受到一个半正弦冲击的峰值加速度取决于电池的质量。对于小型电池，脉冲持续时间为6毫秒，对于大型电池，脉冲时间为11毫秒。下面提供的公式用来计算适当的最小峰值加速度。</p> | | P | | | | | | | | | | |
| | <table><tr><th>Battery</th><th>Minimum peak acceleration</th><th>Pulse duration</th></tr><tr><td rowspan="2">Small batteries</td><td>150 gn or result of formula Acceleration(g_n)=$\sqrt{\frac{100850}{\text{mass}^*}}$ Acceleration gn whichever is smaller</td><td rowspan="2">6 ms</td></tr><tr><td>50 gn or result of formula Acceleration(g_n)=$\sqrt{\frac{30000}{\text{mass}^*}}$ Acceleration gn whichever is smaller</td></tr><tr><td>Large batteries</td><td>Acceleration(g_n)=$\sqrt{\frac{30000}{\text{mass}^*}}$ Acceleration gn whichever is smaller</td><td>11 ms</td></tr></table> <p>*Mass is expressed in kilograms</p> | Battery | Minimum peak acceleration | Pulse duration | Small batteries | 150 gn or result of formula Acceleration(g _n)= $\sqrt{\frac{100850}{\text{mass}^*}}$ Acceleration gn whichever is smaller | 6 ms | 50 gn or result of formula Acceleration(g _n)= $\sqrt{\frac{30000}{\text{mass}^*}}$ Acceleration gn whichever is smaller | Large batteries | Acceleration(g _n)= $\sqrt{\frac{30000}{\text{mass}^*}}$ Acceleration gn whichever is smaller | 11 ms | | P |
| Battery | Minimum peak acceleration | Pulse duration | | | | | | | | | | | |
| Small batteries | 150 gn or result of formula Acceleration(g _n)= $\sqrt{\frac{100850}{\text{mass}^*}}$ Acceleration gn whichever is smaller | 6 ms | | | | | | | | | | | |
| | 50 gn or result of formula Acceleration(g _n)= $\sqrt{\frac{30000}{\text{mass}^*}}$ Acceleration gn whichever is smaller | | | | | | | | | | | | |
| Large batteries | Acceleration(g _n)= $\sqrt{\frac{30000}{\text{mass}^*}}$ Acceleration gn whichever is smaller | 11 ms | | | | | | | | | | | |



Report No.: BST20200313695001LBR

| ST/SG/AC.10/11/Rev.6, 38.3/Amendment 1 | | | |
|--|--|-------------|-------------|
| 条款/Clause | 标准要求/ Requirement + Test | 结果 / Result | 判定/ Verdict |
| | <p>Cells and batteries meet this requirement if there is no mass loss, no leakage, no venting, no disassembly, no rupture and no fire and if the open circuit voltage of each test cell or battery after testing is not less than 90% of its voltage immediately prior to this procedure. The requirement relating to voltage is not applicable to test cells and batteries at fully discharged states.</p> <p>/ 电芯和电池符合要求: 无质量损失、无漏液、无冒烟、无分解、无破裂以及无着火现象; 电芯或电池测试后的开路电压不低于测试前开路电压的90%。</p> <p>此项关于电压方面的要求不适用于完全放电后的电芯和电池。</p> | | P |
| 38.3.4.5 | Test T.5: External short circuit/外部短路 | | |
| | <p>The cell or battery to be tested shall be shall be temperature stabilized so that its external case temperature reaches 57±4°C and then the cell or battery shall be subjected to a short circuit condition with a total external resistance of less than 0.1 ohm at 57±4°C. This short circuit condition is continued for at least one hour after the cell or battery external case temperature has returned to 57±4°C. /保持测试环境温度稳定在57±4°C, 以便样品外表温度达到57±4°C, 然后将样品正负极用小于0.1欧姆的总电阻回路进行短路, 样品的外表温度恢复到57±4°C之后保持短路状态1小时以上。</p> | | P |
| | <p>Cells and batteries meet this requirement if their external temperature does not exceed 170 °C and there is no disassembly, no rupture and no fire during the test and within six hours after the test./电芯和电池符合要求: 在测试过程中以及之后6个小时内, 外表温度不超过170°C, 并且无分解、无破裂和无着火现象发生。</p> | | P |
| 38.3.4.6 | Test T.6: Impact / Crush/撞击/挤压 | | P |
| | <p>Test procedure – Impact (applicable to cylindrical cells greater than or equal to 18 mm in diameter) /撞击(适合于直径大于或等于18mm的圆柱形电芯)</p> | | P |



Report No.: BST20200313695001LBR

| ST/SG/AC.10/11/Rev.6, 38.3/Amendment 1 | | | |
|--|--|-------------|-------------|
| 条款/Clause | 标准要求/ Requirement + Test | 结果 / Result | 判定/ Verdict |
| | The sample cell or component cell is to be placed on a flat smooth surface. A 15.8 mm±0.1mm diameter, at least 6 cm long, or the longest dimension of the cell, whichever is greater, Type 316 stainless steel bar is to be placed across the centre of the sample. A 9.1 kg±0.1 kg mass is to be dropped from a height of 61±2.5 cm at the intersection of the bar and sample in a controlled manner using a near frictionless, vertical sliding track or channel with minimal drag on the falling mass. The vertical track or channel used to guide the falling mass shall be oriented 90 degrees from the horizontal supporting surface. /将样品放在一个平坦的光滑平面上。将一直径为15.8 mm±0.1mm，长度不小于6cm的316不锈钢棒横过样品中部放置后，将一质量为9.1 kg±0.1 kg的重物从61±2.5 cm的高度落向样品 | | P |
| | The test sample is to be impacted with its longitudinal axis parallel to the flat surface and perpendicular to the longitudinal axis of the 15.8 mm±0.1mm diameter curved surface lying across the centre of the test sample. Each sample is to be subjected to only a single impact. /接受撞击的样品，纵轴应与平坦的表面平行并与横放在样品中心的直径15.8 mm±0.1mm弯曲表面的纵轴垂直。每一个样品只接受一次撞击。 | | P |
| | Test Procedure – Crush (applicable to prismatic, pouch, coin/button cells and cylindrical cells not more than 18 mm in diameter). /挤压 (适用于棱柱形、袋状、硬币/纽扣电芯和直径不超过18mm的圆柱形电芯) | | N/A |
| | A cell or component cell is to be crushed between two flat surfaces. The crushing is to be gradual with a speed of approximately 1.5 cm/s at the first point of contact. The crushing is to be continued until the first of the three options below is reached. /将样品放在两个平面之间挤压，挤压力度逐渐加大，在第一个接触点上的速度大约为1.5cm/s。挤压持续进行，直到出现以下三种情况之一 | | N/A |
| | (a) The applied force reaches 13kN±0.78kN; /施加力达到13kN±0.78kN | | N/A |
| | (b) The voltage of the cell drops by at least 100 mV; /样品的电压下降至少100mV | | N/A |
| | (c) The cell is deformed by 50% or more of its original thickness. /电池变形达原始厚度的50%以上。 | | N/A |



Report No.: BST20200313695001LBR

| ST/SG/AC.10/11/Rev.6, 38.3/Amendment 1 | | | |
|--|--|-------------|-------------|
| 条款/Clause | 标准要求/ Requirement + Test | 结果 / Result | 判定/ Verdict |
| | A prismatic or pouch cell shall be crushed by applying the force to the widest side. A button/coin cell shall be crushed by applying the force on its flat surfaces. For cylindrical cells, the crush force shall be applied perpendicular to the longitudinal axis. /棱柱形或袋状电芯应从最宽的一面施压。纽扣/硬币形电芯应从其平坦表面施压。圆柱形应从与纵轴垂直的方向施压。 | | N/A |
| | Each test cell or component cell is to be subjected to one crush only. The test sample shall be observed for a further 6 h. The test shall be conducted using test cells or component cells that have not previously been subjected to other tests. /每个样品都是全新样品，并且只经受一次施压。施压结束后样品应静置观察6小时。 | | P |
| | Cells and component cells meet this requirement if their external temperature does not exceed 170°C and there is no disassembly and no fire during the test and within six hours after this test. /电芯满足要求：在测试过程中以及之后6个小时内，外表温度不超过170°C，并且无分解和无着火现象发生。 | | P |
| 38.3.4.7 | Test T.7: Overcharge/过充电 | | P |
| | The charge current shall be twice the manufacturer's recommended maximum continuous charge current. Tests are to be conducted at ambient temperature. The duration of the test shall be 24 hours. The minimum voltage of the test shall be as follows: /在室温下，以2倍的制造商宣称的最大持续充电电流对样品充电，测试时间为24小时。测试的最小电压如下： | | P |
| | (a) When the manufacturer's recommended charge voltage is not more than 18V, the minimum voltage of the test shall be the lesser of two times the maximum charge voltage of the battery or 22V. /如果制造商宣称的充电电压不超过18V，本测试的最小充电电压应是制造商宣称的最大充电电压的两倍或者是22V之中的较小者。 | | P |
| | (b) When the manufacturer's recommended charge voltage is more than 18V, the minimum voltage of the test shall be 1.2 times the maximum charge voltage. /如果制造商宣称的充电电压超过18V，本测试的最小充电电压应该是制造商宣称的最大充电电压的1.2倍。 | | P |



Report No.: BST20200313695001LBR

| ST/SG/AC.10/11/Rev.6, 38.3/Amendment 1 | | | |
|--|---|-------------|-------------|
| 条款/Clause | 标准要求/ Requirement + Test | 结果 / Result | 判定/ Verdict |
| | There is no disassembly and no fire during the test and within seven days after the test. / 在测试中和测试完成后7天内, 样品无分解和无着火现象。 | | P |
| 38.3.4.8 | Test T.8: Forced discharge/强制放电 | | P |
| | Each cell shall be forced discharged at ambient temperature by connecting it in series with a 12V D.C. power supply at an initial current equal to the maximum discharge current specified by the manufacturer. /在室温下, 将单个电芯连接在12V的直流电源上进行强制放电, 此直流电源供给每个电芯初始电流为制造商宣称的最大放电电流。 The specified discharge current is to be obtained by connecting a resistive load of the appropriate size and rating in series with the test cell. Each cell shall be forced discharged for a time interval (in hours) equal to its rated capacity divided by the initial test current (in ampere). /指定的放电电流通过串联在测试电芯上的合适大小和功率的负载来获得, 每个电芯的强制放电时间(小时)为额定容量除以初始电流(安培)。 | | P |
| | There is no disassembly and no fire during the test and within seven days after the test./ 在测试中和测试完成后7天内, 样品无分解和无着火现象发生 | | P |

**T.1. Altitude simulation高度模拟**

| The state of cells 样品状态 | No. 编号 | Pre-test试验前 | | After test试验后 | | Mass loss 质量损失 (%) | Voltage after test/Voltage pre-test 试验后电压/试验前电压 (%) | Status 结果 |
|---|-----------|----------------|-------------------|----------------|-------------------|-----------------------|--|--------------|
| | | Mass 质量 (g) | Voltage 电压 (V) | Mass 质量 (g) | Voltage 电压 (V) | | | |
| at first cycle, in fully charged states 第一次循环后满电状态 | 1# | 586.58 | 25.18 | 586.48 | 25.17 | 0.017 | 99.96 | Pass 合格 |
| | 2# | 586.65 | 25.19 | 586.61 | 25.18 | 0.007 | 99.96 | Pass 合格 |
| | 3# | 586.68 | 25.18 | 586.53 | 25.18 | 0.026 | 100.00 | Pass 合格 |
| | 4# | 586.65 | 25.17 | 586.43 | 25.17 | 0.038 | 100.00 | Pass 合格 |
| | 5# | 586.67 | 25.19 | 586.46 | 25.17 | 0.036 | 99.92 | Pass 合格 |
| after 25 cycles ending in fully charged states 在25次循环后满充状态 | 6# | 586.75 | 25.19 | 586.55 | 25.18 | 0.034 | 99.96 | Pass 合格 |
| | 7# | 585.98 | 25.18 | 585.78 | 25.18 | 0.034 | 100.00 | Pass 合格 |
| | 8# | 586.53 | 25.18 | 586.39 | 25.18 | 0.024 | 100.00 | Pass 合格 |
| | 9# | 586.57 | 25.17 | 586.51 | 25.17 | 0.010 | 100.00 | Pass 合格 |
| | 10# | 587.75 | 25.18 | 587.65 | 25.16 | 0.017 | 99.92 | Pass 合格 |
| Notes 注释: Ambient temperature 环境温度: 21.8℃ | | | | | | | | |

T.2. Thermal test温度试验

| The state of cells 样品状态 | No. 编号 | Pre-test试验前 | | After test试验后 | | Mass loss 质量损失 (%) | Voltage after test/Voltage pre-test 试验后电压/试验前电压 (%) | Status 结果 |
|---|-----------|----------------|-------------------|----------------|-------------------|-----------------------|--|--------------|
| | | Mass 质量 (g) | Voltage 电压 (V) | Mass 质量 (g) | Voltage 电压 (V) | | | |
| at first cycle, in fully charged states 第一次循环后满电状态 | 1# | 586.48 | 25.17 | 585.45 | 25.15 | 0.176 | 99.92 | Pass 合格 |
| | 2# | 586.61 | 25.18 | 585.71 | 25.16 | 0.153 | 99.92 | Pass 合格 |
| | 3# | 586.53 | 25.18 | 585.47 | 25.15 | 0.181 | 99.88 | Pass 合格 |
| | 4# | 586.43 | 25.17 | 585.48 | 25.14 | 0.162 | 99.88 | Pass 合格 |
| | 5# | 586.46 | 25.17 | 585.46 | 25.13 | 0.171 | 99.84 | Pass 合格 |
| after 25 cycles ending in fully charged states 在25次循环后满充状态 | 6# | 586.55 | 25.18 | 586.17 | 25.15 | 0.065 | 99.88 | Pass 合格 |
| | 7# | 585.78 | 25.18 | 585.28 | 25.16 | 0.085 | 99.92 | Pass 合格 |
| | 8# | 586.39 | 25.18 | 585.39 | 25.15 | 0.171 | 99.88 | Pass 合格 |
| | 9# | 586.51 | 25.17 | 585.51 | 25.14 | 0.171 | 99.88 | Pass 合格 |
| | 10# | 587.65 | 25.16 | 586.52 | 25.14 | 0.192 | 99.92 | Pass 合格 |
| Notes 注释: Ambient temperature 环境温度: 22.4℃ | | | | | | | | |



Report No.: BST20200313695001LBR

T.3. Vibration振动

| The state of cells 样品状态 | No. 编号 | Pre-test试验前 | | After test试验后 | | Mass loss 质量损失 (%) | Voltage after test/Voltage pre-test 试验后电压/试验前电压 (%) | Status 结果 |
|---|-----------|----------------|-------------------|----------------|-------------------|-----------------------|--|--------------|
| | | Mass 质量 (g) | Voltage 电压 (V) | Mass 质量 (g) | Voltage 电压 (V) | | | |
| at first cycle, in fully charged states 第一次循环后满电状态 | 1# | 585.45 | 25.15 | 585.42 | 25.15 | 0.005 | 100.00 | Pass 合格 |
| | 2# | 585.71 | 25.16 | 585.62 | 25.15 | 0.015 | 99.96 | Pass 合格 |
| | 3# | 585.47 | 25.15 | 585.42 | 25.15 | 0.009 | 100.00 | Pass 合格 |
| | 4# | 585.48 | 25.14 | 585.44 | 25.14 | 0.007 | 100.00 | Pass 合格 |
| | 5# | 585.46 | 25.13 | 585.42 | 25.12 | 0.007 | 99.96 | Pass 合格 |
| after 25 cycles ending in fully charged states 在25次循环后满充状态 | 6# | 586.17 | 25.15 | 586.17 | 25.15 | 0.000 | 100.00 | Pass 合格 |
| | 7# | 585.28 | 25.16 | 585.28 | 25.15 | 0.000 | 99.96 | Pass 合格 |
| | 8# | 585.39 | 25.15 | 585.33 | 25.15 | 0.010 | 100.00 | Pass 合格 |
| | 9# | 585.51 | 25.14 | 585.42 | 25.14 | 0.015 | 100.00 | Pass 合格 |
| | 10# | 586.52 | 25.14 | 586.52 | 25.14 | 0.000 | 100.00 | Pass 合格 |
| Notes 注释: Ambient temperature 环境温度: 23.0℃ | | | | | | | | |

T.4. Shock冲击

| The state of cells 样品状态 | No. 编号 | Pre-test试验前 | | After test试验后 | | Mass loss 质量损失 (%) | Voltage after test/Voltage pre-test 试验后电压/试验前电压 (%) | Status 结果 |
|---|-----------|----------------|-------------------|----------------|-------------------|-----------------------|--|--------------|
| | | Mass 质量 (g) | Voltage 电压 (V) | Mass 质量 (g) | Voltage 电压 (V) | | | |
| at first cycle, in fully charged states 第一次循环后满电状态 | 1# | 585.42 | 25.15 | 585.32 | 25.15 | 0.017 | 100.00 | Pass 合格 |
| | 2# | 585.62 | 25.15 | 585.57 | 25.14 | 0.009 | 99.96 | Pass 合格 |
| | 3# | 585.42 | 25.15 | 585.42 | 25.15 | 0.000 | 100.00 | Pass 合格 |
| | 4# | 585.44 | 25.14 | 585.29 | 25.14 | 0.026 | 100.00 | Pass 合格 |
| | 5# | 585.42 | 25.12 | 585.42 | 25.12 | 0.000 | 100.00 | Pass 合格 |
| after 25 cycles ending in fully charged states 在25次循环后满充状态 | 6# | 586.17 | 25.15 | 586.17 | 25.14 | 0.000 | 99.96 | Pass 合格 |
| | 7# | 585.28 | 25.15 | 585.22 | 25.15 | 0.010 | 100.00 | Pass 合格 |
| | 8# | 585.33 | 25.15 | 585.28 | 25.14 | 0.009 | 99.96 | Pass 合格 |
| | 9# | 585.42 | 25.14 | 585.42 | 25.13 | 0.000 | 99.96 | Pass 合格 |
| | 10# | 586.52 | 25.14 | 586.52 | 25.14 | 0.000 | 100.00 | Pass 合格 |
| Notes 注释: Ambient temperature 环境温度: 22.7℃ | | | | | | | | |



Report No.: BST20200313695001LBR

T.5. External short circuit 外部短路

| The state of cells 样品状态 | No. 编号 | External Peak temperature(°C) 电池表面最高温度(°C) | Status 结果 |
|---|-----------|---|--------------|
| at first cycle, in fully charged states 第一次循环后满电状态 | 1# | 57.3 | Pass 合格 |
| | 2# | 57.6 | Pass 合格 |
| | 3# | 58.0 | Pass 合格 |
| | 4# | 58.3 | Pass 合格 |
| | 5# | 57.5 | Pass 合格 |
| after 25 cycles ending in fully charged states 在25次循环后满充状态 | 6# | 57.6 | Pass 合格 |
| | 7# | 57.4 | Pass 合格 |
| | 8# | 58.1 | Pass 合格 |
| | 9# | 57.5 | Pass 合格 |
| | 10# | 57.6 | Pass 合格 |
| Notes 注释: Ambient temperature 环境温度: 22.0°C | | | |

T.6. Test T.6: Impact / Crush/撞击/挤压

| The state of cells 样品状态 | No. 编号 | External Peak temperature(°C) 电池表面最高温度(°C) | Status 结果 |
|---|-----------|---|--------------|
| At first cycle at 50% of the design rated capacity 在第一次充放电周期 后保持额定容量为 50%的荷电状态 | 11# | 24.3 | Pass 合格 |
| | 12# | 23.6 | Pass 合格 |
| | 13# | 22.6 | Pass 合格 |
| | 14# | 23.6 | Pass 合格 |
| | 15# | 24.1 | Pass 合格 |
| After 25 cycles ending at 50% of the design rated capacity 25次充放电周期后保 持额定容量为50%的 荷电状态 | 16# | 23.7 | Pass 合格 |
| | 17# | 22.9 | Pass 合格 |
| | 18# | 23.5 | Pass 合格 |
| | 19# | 23.4 | Pass 合格 |
| | 20# | 23.8 | Pass 合格 |
| Notes 注释: Ambient temperature 环境温度: 21.5°C | | | |



Report No.: BST20200313695001LBR

T.7. Overcharge过充电

| The state of cells 样品状态 | No. 编号 | Status 结果 |
|---|-----------|--------------|
| at first cycle, in fully charged states 第一次循环后满电状态 | 21# | Pass 合格 |
| | 22# | Pass 合格 |
| | 23# | Pass 合格 |
| | 24# | Pass 合格 |
| | 25# | Pass 合格 |
| after 25 cycles ending in fully charged states 在25次循环后满充状态 | 26# | Pass 合格 |
| | 27# | Pass 合格 |
| | 28# | Pass 合格 |
| | 29# | Pass 合格 |
| | 30# | Pass 合格 |
| Notes 注释: Ambient temperature 环境温度: 22.3℃ Note 注释: DC power supply test-protect the DC 直流电源测试-保护 | | |

T.8. Forced discharge强制放电

| The state of cells 样品状态 | No. 编号 | Status 结果 |
|--|-----------|--------------|
| at first cycle, in fully discharged states 第一次循环后完全放电状态 | 31# | Pass 合格 |
| | 32# | Pass 合格 |
| | 33# | Pass 合格 |
| | 34# | Pass 合格 |
| | 35# | Pass 合格 |
| | 36# | Pass 合格 |
| | 37# | Pass 合格 |
| | 38# | Pass 合格 |
| | 39# | Pass 合格 |
| after 25 cycles ending in fully discharged states 在25次循环后完全放电状态 | 40# | Pass 合格 |
| | 41# | Pass 合格 |
| | 42# | Pass 合格 |
| | 43# | Pass 合格 |
| | 44# | Pass 合格 |
| | 45# | Pass 合格 |
| | 46# | Pass 合格 |
| | 47# | Pass 合格 |
| | 48# | Pass 合格 |
| Notes 注释: Ambient temperature 环境温度: 22.1℃ | | |

样品图片 Photo Documentation





Report No.: BST20200313695001LBR

声 明 Statement

1、本报告无本单位报告专用章和批准人签章无效。

This report is invalid without the special seal for report of BST and the signatures of approver.

2、本报告涂改和删除无效。

This report is invalid if is blotted out and deleted.

3、委托单位对检测结果有异议，应于收到报告之日起十五日内向我司提出。

If the applicant has any questions about results, shall submit to BST within 15 days.

4、本报告仅对客户所送样品负责。

This report is responsible for the sample provided by the client only.

5、未经本单位许可，不得部分复制、摘用本报告书内容。

This report shall not be reproduced except in full, or extracted, without the written approval of BST.

6、客户必须如实提供样品及资料，否则本单位不承担任何相关责任。

The client should provide samples and relevant data, otherwise we will not bear any relevant responsibilities.

--End of test report--