

THERMOFIT® RT-375 TUBING

Fluoropolymer, Semi-Flexible, Clear, Flame Retarded, Heat-Shrinkable

1. SCOPE

This specification covers the requirements for one type of flexible, flame retarded, electrical insulating, extruded tubing whose diameter will reduce to a predetermined size upon the application of heat in excess of $150\pm C$ ($302\pm F$). The tubing shall be flame retarded and shall be clear.

2. APPLICABLE DOCUMENTS

This specification takes precedence over documents referenced herein. Unless otherwise specified, the latest issue of referenced documents applies. The following documents form a part of this specification to the extent specified herein.

2.1 GOVERNMENT-FURNISHED DOCUMENTS

Federal

O-S-1926 Sodium Chloride, Technical

Military

MIL-H-5606 Hydraulic Fluid, Petroleum Base, Aircraft, Missile and Ordnance

MIL-T-5624 Turbine Fuel, Aviation, Grades JP-4 and JP-5

MIL-L-7808 Lubricating Oil, Aircraft Turbine Engine, Synthetic Base

MIL-A-8243 Anti-icing and Deicing - Defrosting Fluid

MIL-I-23053 Insulating Sleeving, Electrical, Heat Shrinkable, General Specification for

MIL-L-23699 Lubricating Oil, Aircraft Turbine Engines, Synthetic Base

2.2 OTHER PUBLICATIONS

American Society for Testing and Materials (ASTM)

D 2671 Standard Methods of Testing Heat-Shrinkable Tubing for Electrical Use

G 21 Standard Recommended Practice for Determining Resistance of Synthetic Polymeric Materials to Fungi

(Copies of ASTM publications may be obtained from the American Society for Testing and Materials, 1916 Race Street, Philadelphia, Pennsylvania 19103.)

3. REQUIREMENTS

3.1 MATERIALS

The tubing shall be fabricated from thermally stabilized, modified fluoropolymer and shall be crosslinked by irradiation. It shall be homogeneous and essentially free from flaws, defects, pinholes, bubbles, seams, cracks, and contaminants.

3.2 PROPERTIES

The tubing shall meet the requirements of Table 3.

4. QUALITY ASSURANCE PROVISIONS

4.1 CLASSIFICATION OF TESTS

4.1.1 Qualification Tests

Qualification tests are those performed on tubing submitted for qualification as a satisfactory product and shall consist of all tests listed in this specification.

4.1.2 Acceptance Tests

Acceptance tests are those performed on tubing submitted for acceptance under contract. Acceptance tests shall be:

Dimensions
Longitudinal Change
Concentricity
Tensile Strength
Ultimate Elongation
Secant Modulus
Low Temperature Flexibility
Flammability
Heat Shock
Clarity Stability

4.2 SAMPLING INSTRUCTIONS

4.2.1 Qualification Test Samples

Qualification test samples shall consist of 50 feet (15 m) of tubing. Qualification of any size within each size range specified below shall qualify all sizes within that size range.

Range of Sizes

3/64 through 1/4

3/8 through 1

4.2.2 Acceptance Test Samples

Acceptance test samples shall consist of not less than 16 feet (5 m) of tubing selected at random from each lot.

4.2.3 Lot Formation

A lot shall consist of all tubing of the same size, from the same production run, and offered for inspection at the same time.

4.3 TEST PROCEDURES

Unless otherwise specified, perform tests on specimens which have been fully recovered by conditioning for 3 minutes in a $200 \pm 5\pm C$ ($392 \pm 9\pm F$) oven. Condition the test specimens (and measurement gauges, when applicable) for 3 hours at $23 \pm 3\pm C$ ($73 \pm 5\pm F$) and 50 ± 5 percent relative humidity prior to all testing. Use mechanical convection type ovens in which air passes the specimens at a velocity of 100 to 200 feet (30 to 60 m) per minute.

4.3.1 Low Temperature Flexibility

For tubing of expanded diameter less than 1/4 inch (6 mm), cut three tubular specimens, 12 inches (300 mm) long, from the expanded tubing. For tubing of expanded diameter 1/4 inch (6 mm) or greater, cut three strip specimens, 1/4 inch (6 mm) wide and 12 inches (300 mm) long, from the expanded tubing. Recover the specimens in accordance with Section 4.3 and condition with appropriate mandrels for 4 hours at $-55 \pm 2\pm C$ ($-67 \pm 4\pm F$). The mandrel diameter shall be 10 times the specimen thickness, ± 10 percent. For tubular specimens, the specimen thickness shall be equivalent to the outside diameter. While at the specified temperature, and without removing the specimens from the cold chamber, wrap the specimens $360\pm$ around the mandrel in approximately 2 seconds. Disregard any side cracking, caused by flattening of the specimens on the mandrel.

4.4 REJECTION AND RETEST

Failure of any sample of tubing to conform to any one of the requirements of this specification shall be cause for rejection of the lot represented. Tubing which has been rejected may be replaced or reworked to correct the defects and resubmitted for acceptance. Before resubmitting, full particulars concerning previous rejection and action taken to correct the defects shall be furnished to the inspector.

5. PREPARATION FOR DELIVERY**5.1 FORM**

The tubing shall be supplied on spools, unless otherwise specified.

5.2 PACKAGING

Packaging shall be in accordance with good commercial practice.

5.3 MARKING

Each container of tubing shall be permanently and legibly marked with the size, quantity, manufacturer's name, product name, and lot number.

TABLE 1
Tubing Dimensions

Size	As Supplied		As Recovered							
	Inside Diameter Minimum		Inside Diameter Maximum		Wall Thickness					
					Minimum		Maximum		Nominal	
	in.	mm.	in.	mm.	in.	mm.	in.	mm.	in.	mm.
3/64	.046	1.17	.023	0.58	.008	0.20	.012	0.30	.010	0.25
1/16	.063	1.60	.031	0.79	.008	0.20	.012	0.30	.010	0.25
3/32	.093	2.36	.046	1.17	.008	0.20	.012	0.30	.010	0.25
1/8	.125	3.17	.062	1.57	.008	0.20	.012	0.30	.010	0.25
3/16	.187	4.74	.093	2.36	.008	0.20	.012	0.30	.010	0.25
1/4	.250	6.35	.125	3.17	.009	0.23	.015	0.38	.012	0.30
3/8	.375	9.50	.187	4.74	.009	0.23	.015	0.38	.012	0.30
1/2	.500	12.70	.250	6.35	.009	0.23	.015	0.38	.012	0.30
3/4	.750	19.05	.375	9.50	.014	0.36	.020	0.51	.017	0.43
1	1.000	25.40	.500	12.70	.016	0.41	.022	0.56	.019	0.48

TABLE 2
Mandrel Dimensions for Bend Testing

Tubing Size	Mandrel Diameter	
	in.	mm.
3/64 to 1/4 inclusive	5/16 ± 0.002	7.9 ± 0.05
3/8 to 1/2 inclusive	3/8 ± 0.003	9.5 ± 0.08
3/4 to 1 inclusive	7/16 ± 0.004	11.1 ± 0.10

TABLE 3
Requirements

PROPERTY	UNIT	REQUIREMENT	TEST METHOD
PHYSICAL			
Dimensions	Inches (<i>mm</i>)	In accordance with Table 1	ASTM D 2671
Longitudinal Change	Percent	+0, -10	Note 1
Tensile Strength	psi (<i>MPa</i>)	3500 (<i>24.1</i>) minimum	ASTM D 2671
Ultimate Elongation	Percent	300 minimum	Note 2
Concentricity	Percent	70 minimum	MIL-I-23053
Secant Modulus (Expanded)	psi (<i>MPa</i>)	2.5×10^4 (<i>172</i>) minimum	ASTM D 2671
Specific Gravity	---	1.90 maximum	ASTM D 2671
Low Temperature Flexibility 4 hours at $-55 \pm 2\text{C}$ ($-67 \pm 4\text{F}$)	---	No cracking	Section 4.3.1
Heat Shock 4 hours at $250 \pm 3\text{C}$ ($482 \pm 5\text{F}$)	---	No dripping, flowing or cracking	Table 2 ASTM D 2671
Heat Resistance 336 hours at $225 \pm 3\text{C}$ ($437 \pm 5\text{F}$) Followed by test for: Ultimate Elongation	Percent	100 minimum	ASTM D 2671
Clarity Stability 24 hours at $200 \pm 3\text{C}$ ($392 \pm 5\text{F}$)	---	Marking legible through tubing wall	MIL-I-23053
ELECTRICAL			
Dielectric Strength	Volts/mil (volts/mm)	400 (<i>15,760</i>) minimum <u>= 15KV/mm</u>	ASTM D 2671 Note 3
Volume Resistivity	ohm-cm	10^{11} minimum	ASTM D 2671
CHEMICAL			
Copper Mirror Corrosion 16 hours at $160 \pm 2\text{C}$ ($320 \pm 4\text{F}$)	---	Noncorrosive	ASTM D 2671 Procedure A
Copper Contact Corrosion 16 hours at $160 \pm 2\text{C}$ ($320 \pm 4\text{F}$)	---	No pitting or blackening of copper	ASTM D 2671 Procedure B
Flammability	---	Self-extinguishing within 1 minute, 25% maximum flag burn	ASTM D 2671 Procedure C
Fungus Resistance	---	Rating of 0	ASTM G 21

NOTE 1: Condition the specimens for 3 minutes at $200 \pm 3\text{C}$ ($392 \pm 5\text{F}$) and cool to room temperature before final measurements.

NOTE 2: Use 1-inch (*25.4-mm*) bench marks, 1-inch (*25.4-mm*) initial jaw separation, and $2 \pm .2$ -inch ($50 \pm 5\text{-mm}$) jaw separation speed.

NOTE 3: Recover the specimens on the metal mandrels for 10 minutes, minimum, at $175 \pm 2\text{C}$ ($347 \pm 4\text{F}$) or until the tubing is completely shrunk on the mandrels.

NOTE 4: To measure the dielectric strength, immerse the recovered specimens in the fluids prior to inserting the mandrels into the wiped and dried specimens.

TABLE 3
Requirements (continued)

PROPERTY	UNIT	REQUIREMENT	TEST METHOD
Water Absorption 24 hours at $23 \pm 3 \pm C$ ($73 \pm 5 \pm F$)	Percent	0.5 maximum	ASTM D 2671
Fluid Resistance 24 hours at $50 \pm 3 \pm C$ ($122 \pm 5 \pm F$) in: JP-4 Fuel (MIL-T-5624) Hydraulic Fluid (MIL-H-5606) Lubricating Oil, (MIL-L-23699) Lubricating Oil, (MIL-L-7808) 5% NaCl, O-S-1926 De-icing Fluid (MIL-A-8243) Water Followed by tests for:	---	---	ASTM D 2671 Note 4
Tensile Strength	psi (<i>MPa</i>)	2000 (<i>13.8</i>) minimum	
Ultimate Elongation	Percent	250	
Dielectric Strength	Volts/mil (<i>volts/mm</i>)	400 (<i>15,760</i>) minimum	